



ISO 17025 LABORATORY
TESTING CERT # 2937.01

*Midwest Pooled Fund Research Program
Fiscal Years 2014-2015 (Years 24 through 25)
Research Project Number TPF-5(193) Supplement #64 and #79
NDOT Sponsoring Agency Code RFPF-14-CABLE-1 and RFPF-15-CABLE-1*

MASH TEST NO. 3-10 OF A NON-PROPRIETARY, HIGH-TENSION, CABLE MEDIAN BARRIER FOR USE IN 6H:1V V-DITCH (TEST NO. MWP-9)

Submitted by

Mojdeh Asadollahi Pajouh, Ph.D., P.E.
Post-Doctoral Research Associate

Karla A. Lechtenberg, M.S.M.E., E.I.T.
Research Engineer

Ronald K. Faller, Ph.D., P.E.
Research Associate Professor
MwRSF Director

James C. Holloway
Assistant Director – Physical Testing Division

Robert W. Bielenberg, M.S.M.E., E.I.T.
Research Engineer

Scott K. Rosenbaugh, M.S.C.E., E.I.T.
Research Engineer

John D. Reid, Ph.D.
Professor

MIDWEST ROADSIDE SAFETY FACILITY

Nebraska Transportation Center
University of Nebraska-Lincoln

Main Office

Prem S. Paul Research Center at Whittier School
Room 130, 2200 Vine Street
Lincoln, Nebraska 68583-0853
(402) 472-0965

Outdoor Test Site

4630 N.W. 36th Street
Lincoln, Nebraska 68524

Submitted to

MIDWEST POOLED FUND PROGRAM

Nebraska Department of Transportation
1500 Nebraska Highway 2
Lincoln, Nebraska 68502

MwRSF Research Report No. TRP-03-360-18

March 30, 2018

DISCLAIMER STATEMENT

This report was completed with funding from the Federal Highway Administration, U.S. Department of Transportation and the Midwest Pooled Fund Program. The contents of this report reflect the views and opinions of the authors who are responsible for the facts and the accuracy of the data presented herein. The contents do not necessarily reflect the official views or policies of the state highway departments participating in the Midwest Pooled Fund Program nor the Federal Highway Administration, U.S. Department of Transportation. This report does not constitute a standard, specification, regulation, product endorsement, or an endorsement of manufacturers.

UNCERTAINTY OF MEASUREMENT STATEMENT

The Midwest Roadside Safety Facility (MwRSF) has determined the uncertainty of measurements for several parameters involved in standard full-scale crash testing and non-standard testing of roadside safety features. Information regarding the uncertainty of measurements for critical parameters is available upon request by the sponsor and the Federal Highway Administration.

INDEPENDENT APPROVING AUTHORITY

The Independent Approving Authority (IAA) for the data contained herein was Dr. Jennifer Schmidt, P.E., Research Assistant Professor.

ACKNOWLEDGEMENTS

The authors wish to acknowledge several sources that made a contribution to this project: (1) the Midwest Pooled Fund Program funded by the California Department of Transportation, Florida Department of Transportation, Illinois Department of Transportation, Indiana Department of Transportation, Iowa Department of Transportation, Kansas Department of Transportation, Kentucky Department of Transportation, Minnesota Department of Transportation, Missouri Department of Transportation, Nebraska Department of Transportation, New Jersey Department of Transportation, North Carolina Department of Transportation, Ohio Department of Transportation, South Carolina Department of Transportation, South Dakota Department of Transportation, Utah Department of Transportation, Virginia Department of Transportation, Wisconsin Department of Transportation, and Wyoming Department of Transportation for sponsoring this project; and (2) MwRSF personnel for constructing the barrier and conducting the crash test.

Acknowledgement is also given to the following individuals who made a contribution to the completion of this research project.

Midwest Roadside Safety Facility

J.D. Schmidt, Ph.D., P.E., Research Assistant Professor
C.S. Stolle, Ph.D., Research Assistant Professor
S.A. Ranjha, Ph.D., Post-Doctoral Research Associate
A.T. Russell, B.S.B.A., Testing and Maintenance Technician II
E.W. Krier, B.S., Construction and Testing Technician II
S.M. Tighe, Construction and Testing Technician I
D.S. Charroin, Construction and Testing Technician I
M.A. Rasmussen, Construction and Testing Technician I
J.E. Kohtz, B.S.M.E., CAD Technician
E.L. Urbank, B.A., Research Communication Specialist
Undergraduate and Graduate Research Assistants

California Department of Transportation

Bob Meline, Chief, Roadside Safety Research Branch
David Whitesel, P.E., Transportation Engineer
John Jewell, P.E., Senior Transportation Engineer, Specialist

Florida Department of Transportation

Derwood C. Sheppard, Jr., P.E., Design Standards Publication Manager, Roadway Design Engineer

Illinois Department of Transportation

Priscilla A. Tobias, P.E., State Safety Engineer/Bureau Chief
Paul L. Lorton, P.E., Safety Programs Unit Chief
Filiberto Sotelo, Safety Evaluation Engineer

Indiana Department of Transportation

Todd Shields, P.E., Maintenance Field Support Manager
Katherine Smutzer, P.E., Standards Engineer

Iowa Department of Transportation

Chris Poole, P.E., Roadside Safety Engineer
Brian Smith, P.E., Methods Engineer
Daniel Harness, P.E., Transportation Engineer Specialist

Kansas Department of Transportation

Ron Seitz, P.E., Bureau Chief
Scott King, P.E., Road Design Bureau Chief
Brandon Vacek, P.E., Road Squad Leader, Bureau of Road Design
Thomas Rhoads, P.E., Engineering Associate III, Bureau of Road Design

Kentucky Department of Transportation

Jason J. Siwula, P.E., Assistant State Highway Engineer

Minnesota Department of Transportation

Michael Elle, P.E., Design Standards Engineer
Michelle Moser, P.E., Assistant Design Standards Engineer

Missouri Department of Transportation

Ronald Effland, P.E., ACTAR, LCI, Non-Motorized Transportation Engineer

Nebraska Department of Transportation

Phil TenHulzen, P.E., Design Standards Engineer
Jim Knott, P.E., Construction Engineer
Mark Osborn, P.E., Secondary Roads Engineer
Mike Owen, P.E., Roadway Design Engineer
Jodi Gibson, Research Coordinator

New Jersey Department of Transportation

Dave Bizuga, Senior Executive Manager, Roadway Design Group 1

North Carolina Department of Transportation

Neil Mastin, P.E., Manager, Transportation Program Management – Research and Development
D. D. “Bucky” Galloway, P.E., CPM, Field Operations Engineer
Brian Mayhew, P.E., State Traffic Safety Engineer
Joel Howerton, P.E., Plans and Standards Engineer

Ohio Department of Transportation

Don Fisher, P.E., Roadway Standards Engineer

South Carolina Department of Transportation

Mark H. Anthony, P.E., Letting Preparation Engineer

South Dakota Department of Transportation

David Huft, P.E., Research Engineer
Bernie Clocksin, P.E., Lead Project Engineer

Utah Department of Transportation

Shawn Debenham, Traffic and Safety Specialist
Glenn Blackwelder, Operations Engineer

Virginia Department of Transportation

Charles Patterson, P.E., Standards/Special Design Section Manager
Andrew Zickler, P.E., Complex Bridge Design and ABC Support Program Manager

Wisconsin Department of Transportation

Jerry Zogg, P.E., Chief Roadway Standards Engineer
Erik Emerson, P.E., Standards Development Engineer
Rodney Taylor, P.E., Roadway Design Standards Unit Supervisor

Wyoming Department of Transportation

William Wilson, P.E., Architectural and Highway Standards Engineer

Federal Highway Administration

David Mraz, Division Bridge Engineer, Nebraska Division Office
Danny Briggs, Nebraska Division Office

TABLE OF CONTENTS

TECHNICAL REPORT DOCUMENTATION PAGE ii

DISCLAIMER STATEMENT iii

UNCERTAINTY OF MEASUREMENT STATEMENT iii

INDEPENDENT APPROVING AUTHORITY..... iii

ACKNOWLEDGEMENTS iv

TABLE OF CONTENTS..... vii

LIST OF FIGURES ix

LIST OF TABLES xiii

1 INTRODUCTION 1

 1.1 Background 1

 1.2 Objective 2

 1.3 Scope..... 2

2 TEST REQUIREMENTS AND EVALUATION CRITERIA 3

 2.1 Test Requirements 3

 2.2 Evaluation Criteria 4

 2.3 Soil Strength Requirements 5

3 DESIGN DETAILS 6

4 TEST CONDITIONS..... 40

 4.1 Test Facility 40

 4.2 Vehicle Tow and Guidance System 40

 4.3 Test Vehicle 40

 4.4 Simulated Occupant 45

 4.5 Data Acquisition Systems 45

 4.5.1 Accelerometers 45

 4.5.2 Rate Transducers..... 45

 4.5.3 Retroreflective Optic Speed Trap 45

 4.5.4 Load Cells and String Potentiometers..... 46

 4.5.5 Digital Photography 46

5 FULL-SCALE CRASH TEST NO. MWP-9 49

 5.1 Static Soil Test 49

 5.2 Weather Conditions 49

 5.3 Test Description 49

 5.4 Barrier Damage..... 52

 5.5 Vehicle Damage..... 53

 5.6 Occupant Risk..... 54

5.7 Load Cells and String Potentiometer 55
5.8 Discussion 57

6 SUMMARY AND CONCLUSIONS 105

7 REFERENCES 107

8 APPENDICES 109

 Appendix A. Material Specifications 110
 Appendix B. Vehicle Center of Gravity Determination..... 147
 Appendix C. Static Soil Tests 149
 Appendix D. Vehicle Deformation Records 152
 Appendix E. Accelerometer and Rate Transducer Data Plots, Test No. MWP-9..... 160
 Appendix F. Load Cell and String Potentiometer Data 177

LIST OF FIGURES

Figure 1. System Layout, Test No. MWP-9	7
Figure 2. Cable Splice Location and Detail, Test No. MWP-9	8
Figure 3. Cable End Terminal Detail, Test No. MWP-9	9
Figure 4. Cable Anchor Detail, Test No. MWP-9	10
Figure 5. Load Cell and Turnbuckle Configuration, Test No. MWP-9	11
Figure 6. Load Cell Assembly Component Details, Test No. MWP-9	12
Figure 7. Cable Anchor Detail, Post Nos. 1 and 76, Test No. MWP-9	13
Figure 8. Cable Anchor Bracket, Test No. MWP-9	14
Figure 9. Cable Anchor Bracket Components, Test No. MWP-9	15
Figure 10. Cable Release Lever, Test No. MWP-9	16
Figure 11. Second Post Detail, Post Nos. 2 and 75, Test No. MWP-9	17
Figure 12. Cable Hanger Assembly, Post Nos. 2 and 75, Test No. MWP-9	18
Figure 13. Cable Hanger Assembly, Post Nos. 2 and 75, Test No. MWP-9	19
Figure 14. Foundation Tube Assembly, Post Nos. 2 and 75, Test No. MWP-9	20
Figure 15. Midwest Weak Post (MWP) Details, Test No. MWP-9	21
Figure 16. Midwest Weak Post (MWP) Details, Post Nos. 3 through 74, Test No. MWP-9	22
Figure 17. Midwest Weak Post (MWP), Post and Bracket Assembly, Test No. MWP-9	23
Figure 18. Post Nos. 3 through 74, Flat Pattern, Test No. MWP-9	24
Figure 19. Post Cap Details, Post Nos. 3 through 74, Test No. MWP-9	25
Figure 20. Post Cap Flat Patterns, Test No. MWP-9	26
Figure 21. Tabbed Bracket Version 10, Test No. MWP-9	27
Figure 22. Tabbed Bracket Version 10 Flat Pattern, Test No. MWP-9	28
Figure 23. J-Hook Anchor and Brass Cable Clips, Test No. MWP-9	29
Figure 24. Hardware, Test No. MWP-9	30
Figure 25. Bill of Materials, Test No. MWP-9	31
Figure 26. Bill of Materials, Test No. MWP-9	32
Figure 27. System Installation, Test No. MWP-9	33
Figure 28. Post and Cap Details, Test No. MWP-9	34
Figure 29. Bracket Details, Test No. MWP-9	35
Figure 30. Upstream Cable Splices, Test No. MWP-9	36
Figure 31. Downstream Cable Splices, Test No. MWP-9	37
Figure 32. Upstream Anchorage, Test No. MWP-9	38
Figure 33. Downstream Anchorage, Test No. MWP-9	39
Figure 34. Test Vehicle, Test No. MWP-9	41
Figure 35. Test Vehicle's Interior Floorboards, Test No. MWP-9	42
Figure 36. Vehicle Dimensions, Test No. MWP-9	43
Figure 37. Target Geometry, Test No. MWP-9	44
Figure 38. Location of Load Cells and String Potentiometers, Test No. MWP-9	47
Figure 39. Camera Locations, Speeds, and Lens Settings, Test No. MWP-9	48
Figure 40. Cable Tension Loads, Test No. MWP-9	56
Figure 41. Displacement of Upstream Anchor, Test No. MWP-9	57
Figure 42. Summary of Test Results and Sequential Photographs, Test No. MWP-9	58
Figure 43. Sequential Photographs, Test No. MWP-9	59
Figure 44. Sequential Photographs, Test No. MWP-9	60
Figure 45. Additional Sequential Photographs, Test No. MWP-9	61

Figure 46. Impact Location, Test No. MWP-9	62
Figure 47. Vehicle Final Position, Test No. MWP-9.....	63
Figure 48. Vehicle Trajectory, Test No. MWP-9	64
Figure 49. System Damage, Test No. MWP-9	65
Figure 50. Post Nos. 21 through 27 Damage, Test No. MWP-9	66
Figure 51. Post Nos. 28 through 33 Damage, Test No. MWP-9	67
Figure 52. Post Nos. 34 through 43 Damage, Test No. MWP-9	68
Figure 53. Post Nos. 44 through 51 Damage, Test No. MWP-9	69
Figure 54. Post No. 22 Damage, Test No. MWP-9	70
Figure 55. Post No. 23 Damage, Test No. MWP-9	71
Figure 56. Post No. 24 Damage, Test No. MWP-9	72
Figure 57. Post No. 25 Damage, Test No. MWP-9	73
Figure 58. Post No. 26 Damage, Test No. MWP-9	74
Figure 59. Post No. 27 Damage, Test No. MWP-9	75
Figure 60. Post No. 28 Damage, Test No. MWP-9	76
Figure 61. Post No. 29 Damage, Test No. MWP-9	77
Figure 62. Post No. 30 Damage, Test No. MWP-9	78
Figure 63. Post No. 31 Damage, Test No. MWP-9	79
Figure 64. Post No. 32 Damage, Test No. MWP-9	80
Figure 65. Post No. 33 Damage, Test No. MWP-9	81
Figure 66. Post No. 34 Damage, Test No. MWP-9	82
Figure 67. Post No. 35 Damage, Test No. MWP-9	83
Figure 68. Post No. 36 Damage, Test No. MWP-9	84
Figure 69. Post No. 37 Damage, Test No. MWP-9	85
Figure 70. Post No. 38 Damage, Test No. MWP-9	86
Figure 71. Post No. 39 Damage, Test No. MWP-9	87
Figure 72. Post No. 40 Damage, Test No. MWP-9	88
Figure 73. Post No. 41 Damage, Test No. MWP-9	89
Figure 74. Post No. 42 Damage, Test No. MWP-9	90
Figure 75. Post No. 43 Damage, Test No. MWP-9	91
Figure 76. Post No. 44 Damage, Test No. MWP-9	92
Figure 77. Post No. 45 Damage, Test No. MWP-9	93
Figure 78. Post No. 46 Damage, Test No. MWP-9	94
Figure 79. Post No. 47 Damage, Test No. MWP-9	95
Figure 80. Post No. 48 Damage, Test No. MWP-9	96
Figure 81. Post No. 49 Damage, Test No. MWP-9	97
Figure 82. Post No. 50 Damage, Test No. MWP-9	98
Figure 83. Post No. 51 Damage, Test No. MWP-9	99
Figure 84. Post Nos. 52 and 53 Damage, Test No. MWP-9	100
Figure 85. Anchorage Damage, Test No. MWP-9.....	101
Figure 86. Vehicle Damage, Test No. MWP-9.....	102
Figure 87. Vehicle Damage, Test No. MWP-9.....	103
Figure 88. Vehicle Damage, Floor pan, Test No. MWP-9	104
Figure A-1. ³ / ₁₆ -in. (5-mm) Brass Rod, Test No. MWP-9	113
Figure A-2. CMB High Tension Anchor Plate Washer, Test No. MWP-9	114
Figure A-3. ³ / ₄ -in (19-mm) Dia. Flat Washer, Test No. MWP-9	115
Figure A-4. J-Hook Anchor Bolts, Test No. MWP-9.....	116

Figure A-5. 3/4-in. (19-mm) Dia. Heavy Hex Nut, Test No. MWP-9.....117

Figure A-6. 5/8-in. (16-mm) Dia. Heavy Hex Nut, Test No. MWP-9118

Figure A-7. 5/8-in. (16-mm) Dia. UNC, 9 1/2-in. (241-mm) Long Hex Bolt, Test No. MWP-9119

Figure A-8. Concrete Anchor, Test No. MWP-9.....120

Figure A-9. #11 Rebar for Anchorage, Test No. MWP-9121

Figure A-10. #4 Rebar for Anchorage, Test No. MWP-9122

Figure A-11. S3x5.7 (S76x8.5) Posts – 28 1/8 in. (714 mm) and 19 in. (483 mm) Long, Test No. MWP-9.....123

Figure A-12. #3 Rebar for Anchorage, Test No. MWP-9124

Figure A-13. 7/4-in. (184-mm) Dia. #3 Hoop Rebar, Test No. MWP-9125

Figure A-14. 1/2-in. (13-mm) Washers, Test No. MWP-9.....126

Figure A-15. Hex Bolts and Nuts – 1/2-in. (13-mm) Dia. UNC, 2-in. (51-mm) Long and 3/4-in. (19-mm) Dia. UNC, 5 1/2-in. (140-mm) Long, Test No. MWP-9127

Figure A-16. Foundation Tube, Test No. MWP-9.....128

Figure A-17. 2nd Post Cable Hanger, 1/2 in. (13 mm) Thick, Test No. MWP-9129

Figure A-18. 12-in. (305-mm) Dia. 2nd Post Concrete Anchor, Test No. MWP-9130

Figure A-19. 2nd Post Base Plate, 3/8 in. (10 mm) Thick, Test No. MWP-9.....131

Figure A-20. 3x1 3/4x7-gauge (76x44x4.6 mm), 81 1/4-in. (2,064 mm) Long Midwest Weak Post with Holes, Post Nos. 3 through 25 and 62 through 74, Test No. MWP-9.....132

Figure A-21. 3x1 3/4x7-gauge (76x44x4.6 mm), 81 1/4-in. (2,064 mm) Long Midwest Weak Post with Holes, Post Nos. 26 through 61, Test No. MWP-9.....133

Figure A-22. 12-gauge Tabbed Bracket, Version 10, Test No. MWP-9134

Figure A-23. 5/16-in. (8-mm) Dia. UNC, 1-in. (25-mm) Long Hex Cap Screw, Test No. MWP-9.....135

Figure A-24. 5/16-in. (8-mm) Nut, Test No. MWP-9.....136

Figure A-25. 2 1/8"x1 3/8"x7 Gauge [54x35x4.6], 6" [152] Long Bent Steel Plate, Test No. MWP-9.....137

Figure A-26. Brass Straight Rod – 3/16-in. (5-mm) Cable Clip, Test No. MWP-9.....138

Figure A-27. 3/4-in. (19-mm) Diameter 3x7 Cable Guiderail, Test No. MWP-9139

Figure A-28. 3/4-in. (19-mm) Diameter 3x7 Cable Guiderail, Test No. MWP-9140

Figure A-29. 7/8-in. (22-mm) Dia. Hex Nut, Test No. MWP-9.....141

Figure A-30. Cable End Threaded Rod, Test No. MWP-9.....142

Figure A-31. Bennett Cable End Fitter, H# 9Q4, Test No. MWP-9.....143

Figure A-32. Bennett Cable End Fitter, H# OP5, Test No. MWP-9144

Figure A-33. Cable Wedges, Test No. MWP-9.....145

Figure A-34. Bennet Short Threaded Turnbuckle, Test No. MWP-9.....146

Figure B-1. Vehicle Mass Distribution, Test No. MWP-9148

Figure C-1. Soil Strength, Initial Calibration Tests, Test No. MWP-9150

Figure C-2. Static Soil Test, Test No. MWP-9.....151

Figure D-1. Floor pan Deformation Data – Set 1, Test No. MWP-9.....153

Figure D-2. Floor pan Deformation Data – Set 2, Test No. MWP-9.....154

Figure D-3. Occupant Compartment Deformation Data – Set 1, Test No. MWP-9.....155

Figure D-4. Occupant Compartment Deformation Data – Set 2, Test No. MWP-9.....156

Figure D-5. Exterior Vehicle Crush (NASS) - Front, Test No. MWP-9157

Figure D-6. Exterior Vehicle Crush (NASS) - Side, Test No. MWP-9.....158

Figure D-7. A-Pillar Measurements, Test No. MWP-9159

Figure E-1. 10-ms Average Longitudinal Deceleration (SLICE-1), Test No. MWP-9.....161

Figure E-2. Longitudinal Occupant Velocity (SLICE-1), Test No. MWP-9.....162
Figure E-3. Longitudinal Occupant Displacement (SLICE-1), Test No. MWP-9.....163
Figure E-4. 10-ms Average Lateral Deceleration (SLICE-1), Test No. MWP-9164
Figure E-5. Lateral Occupant Impact Velocity (SLICE-1), Test No. MWP-9.....165
Figure E-6. Lateral Occupant Displacement (SLICE-1), Test No. MWP-9.....166
Figure E-7. Vehicle Angular Displacements (SLICE-1), Test No. MWP-9167
Figure E-8. Acceleration Severity Index (SLICE-1), Test No. MWP-9.....168
Figure E-9. 10-ms Average Longitudinal Deceleration (SLICE-2), Test No. MWP-9.....169
Figure E-10. Longitudinal Occupant Impact Velocity (SLICE-2), Test No. MWP-9.....170
Figure E-11. Longitudinal Occupant Displacement (SLICE-2), Test No. MWP-9.....171
Figure E-12. 10-ms Average Lateral Deceleration (SLICE-2), Test No. MWP-9172
Figure E-13. Lateral Occupant Impact Velocity (SLICE-2), Test No. MWP-9173
Figure E-14. Lateral Occupant Displacement (SLICE-2), Test No. MWP-9.....174
Figure E-15. Vehicle Angular Displacements (SLICE-2), Test No. MWP-9175
Figure E-16. Acceleration Severity Index (SLICE-2), Test No. MWP-9.....176
Figure F-1. Load Cell Data, Cable No. 1, Test No. MWP-9178
Figure F-2. Load Cell Data, Cable No. 2, Test No. MWP-9179
Figure F-3. Load Cell Data, Cable No. 3, Test No. MWP-9180
Figure F-4. Load Cell Data, Cable No. 4, Test No. MWP-9181
Figure F-5. String Potentiometer Data, Upstream Anchor, Test No. MWP-9.....182

LIST OF TABLES

Table 1. MASH 2016 TL-3 Test Matrix for Barrier Placement Anywhere Within a 6H:1V
V-Ditch.....4
Table 2. MASH Evaluation Criteria for Longitudinal Barrier.....5
Table 3. Weather Conditions, Test No. MWP-9.....49
Table 4. Sequential Description of Impact Events, Test No. MWP-9.....50
Table 5. Disengaged Cables and Release Mechanisms, Test No. MWP-9.....53
Table 6. Maximum Occupant Compartment Deformations by Location54
Table 7. Summary of OIV, ORA, THIV, PHD, and ASI Values, Test No. MWP-955
Table 8. Maximum Cable Loads, Test No. MWP-9.....55
Table 9. Summary of Safety Performance Evaluation, Test No. MWP-9106
Table A-1. Bill of Materials, Test No. MWP-9111

1 INTRODUCTION

1.1 Background

In recent years, the Midwest Pooled Fund Program has been developing a non-proprietary, high-tension, cable median barrier in conjunction with the Midwest Roadside Safety Facility (MwRSF) [1]. This cable barrier system was intended for use anywhere within a 6H:1V median V-ditch and consisted of four cables supported by Midwest Weak Posts (MWP) spaced at 8 ft intervals (2.4 m). A bolted, tabbed bracket was utilized to attach the lower three cables to alternating sides of the MWPs, while a brass keeper rod was utilized to contain the top cable within a V-notch cut into the top of the posts.

Previously, this cable barrier system was subjected to eight full-scale crash tests in accordance with the *Manual for Assessing Safety Hardware* (MASH) 2009 and 2016 [2-3]. Note that there is no difference between MASH 2009 and MASH 2016 test designation nos. 3-10 and 3-11 for longitudinal barriers, including the cable barriers studied in this research.

Test no. MWP-1, in accordance with MASH 2009 test designation no. 3-17, was conducted with a 1500A mid-size sedan impacting the system on the slope break point of a 6H:1V median V-ditch. During the test, the sedan was successfully captured and redirected by cable no. 2, having overridden cable no. 1 and underridden cable nos. 3 and 4 [1].

For test no. MWP-2, the barrier was placed on level terrain, and the system cables were mirrored so that cable no. 2 was on the impact side of the posts and cable nos. 1 and 3 were on the non-impact side. A 16-ft (4.9-m) post spacing was utilized to evaluate the system's maximum deflection and working width. During the test, the front tires of the 2270P pickup overrode cable nos. 1 and 3. However, cable nos. 2 and 4 successfully captured and contained the vehicle [1].

For test no. MWP-3, the post spacing was changed to 8 ft (2.4 m) to evaluate the system deflections and working width with tighter post spacing. During the test, the 2270P pickup was initially captured by cable nos. 2 and 3 after overriding cable no. 1 and underriding cable no. 4. However, the capture cables were eventually pushed downward and overridden by the left-front tire of the pickup. After containment of the vehicle was lost, the cables wrapped around the left-rear tire and yawed the pickup rapidly toward the barrier. The pickup ultimately rolled over as the right-side tires dug into the ground [1].

Modifications were made to improve the system performance, which required further full-scale crash testing to evaluate the crashworthiness of the system according to the MASH 2009 Test Level 3 (TL-3) criteria [2]. Test no. MWP-4 was conducted in accordance with MASH 2009 test no. 3-11. The barrier was placed on level terrain and utilized a 10-ft (3.0-m) post spacing to establish the working width associated with a reduced post spacing. During the test, the 2270P pickup truck was initially captured and redirected by cable nos. 2 and 4. However, the vehicle eventually overrode cable no. 2 after the vehicle was parallel with the system [4].

Test no. MWP-6, conducted in accordance with MASH 2009 test no. 3-10, involved an 1100C small car impacting the four-cable median barrier system with an 8-ft (2.4-m) post spacing placed on level terrain. During the test, the small car was captured and redirected by cable no. 2. The A-pillar received only 0.12 in. (3 mm) of deformation, as the vehicle underrode cable nos. 3

and 4. The occupant compartment was penetrated when the top of the posts were overridden, causing tears in the floor pan in two locations. Thus, test no. MWP-6 was determined to have failed the safety performance criteria corresponding to MASH 2009 test designation no. 3-10 [4].

To reduce the likelihood of occupant compartment penetration, the top corners of the MWP were rounded. The outer corners were radiused $\frac{5}{8}$ in. (16 mm), and the inner bent corners were filleted $\frac{1}{4}$ in. (6 mm). Test no. MWP-7 was a repeat of test no. MWP-6, but with the modified MWP. During the test, the 1100C small car was captured and redirected by cable no. 2. However, the floor pan was again torn due to contact with the tops of the MWPs as the vehicle overrode them. Four separate tears occurred. Thus, test no. MWP-7 was determined to have failed the safety performance criteria corresponding to MASH 2009 test designation no. 3-10 [4]. These performance issues highlighted the need to develop new barrier components to improve the safety performance of the cable median barrier.

After a series of 21 bogie tests, a modified post was designed to mitigate the floor pan tearing [5]. Test no. MWP-8 was conducted on the modified barrier system, consisting of MWPs with rounded top edges and $\frac{3}{4}$ -in. (19-mm) diameter weakening holes at the ground line. This test was conducted according to MASH 2016 test designation no. 3-10 and utilized an 1100C small car impacting the barrier on a level terrain [6]. The vehicle was contained by the system. No floor pan tearing was observed throughout the initial two vehicle crossover events across the barrier and posts. During the third impact series with the posts, one post penetrated the occupant compartment due to floor pan tearing in two locations. Therefore, test no. MWP-8 was deemed unacceptable.

Investigation into protecting the free edges at the top of the post included adding a cap to the top of the posts to reduce the propensity for post penetration into the occupant compartment and floor pan. A total of five bogie tests were conducted to evaluate several cap designs and post modifications [7]. From the bogie test results, a two-part cap with a single retainer bolt added to the top of the posts was expected to shield the free edges of the top of the MWP during post-to-vehicle contact and mitigate the floor pan tearing.

1.2 Objective

The objective of this report was the evaluation of the safety performance of the modified high-tension cable median barrier in a V-ditch. The system was evaluated according to the TL-3 criteria of the MASH 2016 [2].

1.3 Scope

The research objective was achieved through completion of several tasks. One full-scale crash test was conducted on the modified cable median barrier according to MASH 2016 test designation no. 3-10. Next, the full-scale vehicle crash test results were analyzed, evaluated, and documented. Conclusions and recommendations were then made pertaining to the safety performance of the modified cable median barrier.

2 TEST REQUIREMENTS AND EVALUATION CRITERIA

2.1 Test Requirements

Longitudinal barriers, such as cable median barriers, must satisfy impact safety standards in order to be declared eligible for federal reimbursement by the Federal Highway Administration (FHWA) for use on the National Highway System (NHS). For new hardware, these safety standards consist of the guidelines and procedures published in MASH 2016 [2]. According to TL-3 of MASH 2016, a cable barrier system for use anywhere in a 6H:1V V-ditch must be subjected to eight full-scale vehicle crash tests, as summarized in Table 1.

However, systems with variable post spacing must be conducted with both the narrowest and widest post spacing to bracket the working widths of the barrier system, thereby increasing the required number of crash tests from eight to nine. Note, only one of the prescribed full-scale crash tests, test designation no. 3-10, was conducted and reported herein. Although the impact speed and angle are consistent for all nine tests, the critical location of the barrier system within the median ditch is dependent upon the specific crash test and the slope of the ditch. The MASH 2016 TL-3 testing matrix for a cable median barrier system designed for placement anywhere within a 6H:1V or flatter V-ditch is shown in Table 1.

Many cable barriers have variable post spacing, which allows roadside designers to select the optimal configuration for a specific installation. When evaluating these variable post spacing systems, the critical post spacing should be utilized during crash testing. MASH 2016 has identified the critical post spacing, either the narrowest or the widest spacing, for each individual test within the testing matrix. MASH 2016 test designation no. 3-10 must be conducted with the narrowest post spacing.

In accordance with MASH 2016 requirements, the critical impact point for the 1100C vehicle was determined to be located at the midspan between posts. This impact location was determined to maximize the potential for vehicle penetration by allowing the vehicle to penetrate between cables.

When non-symmetrical cable barriers are tested, it is important to test the orientation that produces the greatest risk of failure. To accomplish this critical evaluation, the orientation of the cables was selected such that primary capture cable would be located on the non-impact side of the post. The primary capture cable for the 1100C vehicle was determined to be the second cable above the ground. Selecting this orientation allowed for the greatest risk of failure delaying vehicle interlock with the barrier and increasing the potential for the vehicle to penetrate through the system.

Table 1. MASH 2016 TL-3 Test Matrix for Barrier Placement Anywhere Within a 6H:1V V-Ditch

Test No.	Test Vehicle	Vehicle Weight, lb (kg)	Impact Conditions		System Configuration		Evaluation Criteria ²
			Speed, mph (km/h)	Angle, deg	System Location ¹	Post Spacing	
3-10	1100C	2,425 (1,100)	62 (100)	25	Level Terrain	Narrow	A,D,F,H,I
3-11	2270P	5,000 (2,270)	62 (100)	25	Level Terrain	Both	A,D,F,H,I
3-13	2270P	5,000 (2,270)	62 (100)	25	9 ft Down Front Slope	Narrow	A,D,F,H,I
3-14	1100C	2,425 (1,100)	62 (100)	25	9 ft Down Front Slope	Narrow	A,D,F,H,I
3-15	1100C	2,425 (1,100)	62 (100)	25	4 ft Up Back Slope	Wide	A,D,F,H,I
3-16	1100C	2,425 (1,100)	62 (100)	25	1 ft Down Back Slope	Narrow	A,D,F,H,I
3-17	1500A	3,300 (1,500)	62 (100)	25	See Note ³	Wide	A,D,F,H,I
3-18	2270P	5,000 (2,270)	62 (100)	25	At Back Slope Break Point	Wide	A,D,F,H,I

¹ Test nos. 3-13 through 3-18 shall be conducted within a 30-ft (9.1-m) wide, 6H:1V V-ditch.

² Evaluation criteria explained in Table 2.

³ Testing laboratory to determine critical barrier position on front slope of ditch to maximize propensity for front end of 1500A vehicle to penetrate between vertically adjacent cables.

2.2 Evaluation Criteria

Evaluation criteria for full-scale vehicle crash testing are based on three appraisal areas: (1) structural adequacy; (2) occupant risk; and (3) vehicle trajectory after collision. Criteria for structural adequacy are intended to evaluate the ability of the cable median barrier to contain and redirect impacting vehicles. In addition, controlled lateral deflection of the test article is acceptable. Occupant risk evaluates the degree of hazard to occupants in the impacting vehicle. Post-impact vehicle trajectory is a measure of the potential of the vehicle to result in a secondary collision with other vehicles and/or fixed objects, thereby increasing the risk of injury to the occupants of the impacting vehicle and/or other vehicles. These evaluation criteria are summarized in Table 2 and defined in greater detail in MASH 2016. The full-scale vehicle crash test documented herein was conducted and reported in accordance with the procedures provided in MASH 2016.

In addition to the standard occupant risk measures, the Post-Impact Head Deceleration (PHD), the Theoretical Head Impact Velocity (THIV), and the Acceleration Severity Index (ASI) were determined and reported on the test summary sheet. Additional discussion on PHD, THIV and ASI is provided in MASH 2016.

Table 2. MASH Evaluation Criteria for Longitudinal Barrier

Structural Adequacy	A. Test article should contain and redirect the vehicle or bring the vehicle to a controlled stop; the vehicle should not penetrate, underride, or override the installation although controlled lateral deflection of the test article is acceptable.		
Occupant Risk	D. Detached elements, fragments or other debris from the test article should not penetrate or show potential for penetrating the occupant compartment, or present an undue hazard to other traffic, pedestrians, or personnel in a work zone. Deformations of, or intrusions into, the occupant compartment should not exceed limits set forth in Section 5.2.2 and Appendix E of MASH 2016.		
	F. The vehicle should remain upright during and after collision. The maximum roll and pitch angles are not to exceed 75 degrees.		
	H. Occupant Impact Velocity (OIV) (see Appendix A, Section A5.2.2 of MASH 2016 for calculation procedure) should satisfy the following limits:		
	Occupant Impact Velocity Limits		
	Component	Preferred	Maximum
Longitudinal and Lateral	30 ft/s (9.1 m/s)	40 ft/s (12.2 m/s)	
Occupant Risk	I. The Occupant Ridedown Acceleration (ORA) (see Appendix A, Section A5.2.2 of MASH for calculation procedure) should satisfy the following limits:		
	Occupant Ridedown Acceleration Limits		
	Component	Preferred	Maximum
	Longitudinal and Lateral	15.0 g's	20.49 g's

2.3 Soil Strength Requirements

In accordance with Chapter 3 and Appendix B of MASH 2016, foundation soil strength must be verified before any full-scale crash testing can occur. During the installation of a soil dependent system, W6x16 (W152x23.8) posts were installed near the impact region utilizing the same installation procedures as the system itself. Prior to full-scale testing, dynamic impact testing was conducted to verify a minimum dynamic soil resistance of 7.5 kips (33.4 kN) at post deflections between 5 and 20 in. (127 and 508 mm) measured at a height of 25 in. (635 mm) above the groundline. If dynamic testing near the system is not desired, MASH 2016 permits a static test to be conducted instead and compared against the results of a previously established baseline test. In this situation, the soil must provide a resistance of at least 90 percent of the static baseline test at deflections of 5, 10, and 15 in. (127, 254, and 381 mm). Further details can be found in Appendix B of MASH 2016.

3 DESIGN DETAILS

The test installation consisted of a 604-ft (184-m) long, four-cable median barrier system, as shown in Figures 1 through 26. Photographs of the test installation are shown in Figures 27 through 33. Material specifications, mill certifications, and certificates of conformity for the system materials are shown in Appendix A.

The cable barrier system consisted of several distinct components: (1) high-tension cables or wire ropes; (2) cable splices; (3) steel support posts; (4) cable-to-post attachment brackets; (5) breakaway end terminals; and (6) reinforced concrete foundations. Four $\frac{3}{4}$ -in. (19-mm) diameter, Class A galvanized 3x7 (pre-stretched) wire ropes were utilized for the longitudinal cables. The cables were placed at heights of 15½ in. (394 mm), 23 in. (584 mm), 30½ in. (775 mm), and 38 in. (965 mm) above the groundline. The cables were numbered 1 through 4, starting with the bottom cable and proceeding upward to the top cable. The cables were tensioned up to a nominal force of 2,500 lb (11.1 kN). These cables were supported by 81¼-in. (2,108-mm) long MWPs modified to include a $\frac{3}{4}$ -in. (19-mm) diameter weakening hole at the groundline and a two-part cap to protect the free edges of the post. Each MWP was fabricated from 7-gauge (4.6-mm) sheet steel bent to a 3-in. x 1¾-in. (76-mm x 44-mm) cross section. The posts were placed on level terrain, spaced 96 in. (2,438 mm) on center with a soil embedment depth of 42 in. (1,067 mm). The posts were installed in a compacted, coarse, crushed, limestone material with a strength that satisfied MASH 2016 criteria.




Figure 1. System Layout, Test No. MWP-9




Figure 2. Cable Splice Location and Detail, Test No. MWP-9

6




Figure 3. Cable End Terminal Detail, Test No. MWP-9




Figure 4. Cable Anchor Detail, Test No. MWP-9




Figure 5. Load Cell and Turnbuckle Configuration, Test No. MWP-9




Figure 6. Load Cell Assembly Component Details, Test No. MWP-9





Figure 7. Cable Anchor Detail, Post Nos. 1 and 76, Test No. MWP-9

	Midwest 4-Cable Barrier System	SHEET: 7 of 26
	Cable Anchor Detail Post Nos. 1 & 76	DATE: 1/26/2018
Midwest Roadside Safety Facility	DWG. NAME: MWP-9_R6	DRAWN BY: JEK
	SCALE: 1:24 UNITS: in./mm	REV. BY: KAL/TJD/MP




Figure 8. Cable Anchor Bracket, Test No. MWP-9




Figure 9. Cable Anchor Bracket Components, Test No. MWP-9





Figure 10. Cable Release Lever, Test No. MWP-9

	Midwest 4-Cable Barrier System	SHEET: 10 of 26
		DATE: 1/26/2018
Midwest Roadside Safety Facility	Cable Release Lever	DRAWN BY: JEK
DWG. NAME: MWP-9_R6	SCALE: 1:5	REV. BY: KAL/TJD/MP
	UNITS: in./mm	




Figure 11. Second Post Detail, Post Nos. 2 and 75, Test No. MWP-9





Figure 12. Cable Hanger Assembly, Post Nos. 2 and 75, Test No. MWP-9



Midwest Roadside Safety Facility

Midwest 4-Cable Barrier System		SHEET: 13 of 26
Cable Hanger Assembly Post Nos. 2 & 75		DATE: 1/26/2018
DWC. NAME: MWP-9_R6		DRAWN BY: JEK
SCALE: 1:8	REV. 9Y: KA-/TUD/ MP	
UNITS: in.[mm]		




Figure 14. Foundation Tube Assembly, Post Nos. 2 and 75, Test No. MWP-9




Figure 15. Midwest Weak Post (MWP) Details, Test No. MWP-9




Figure 16. Midwest Weak Post (MWP) Details, Post Nos. 3 through 74, Test No. MWP-9




Figure 17. Midwest Weak Post (MWP), Post and Bracket Assembly, Test No. MWP-9




Figure 18. Post Nos. 3 through 74, Flat Pattern, Test No. MWP-9




Figure 19. Post Cap Details, Post Nos. 3 through 74, Test No. MWP-9




Figure 20. Post Cap Flat Patterns, Test No. MWP-9




Figure 21. Tabbed Bracket Version 10, Test No. MWP-9




Figure 22. Tabbed Bracket Version 10 Flat Pattern, Test No. MWP-9





Figure 23. J-Hook Anchor and Brass Cable Clips, Test No. MWP-9

	Midwest 4-Cable Barrier System		SHEET: 23 of 26
	J-Hook Anchor and Brass Cable Clip		DATE: 1/26/2018
Midwest Roadside Safety Facility	DWG. NAME: MWP-9_R6		DRAWN BY: JEK
	SCALE: 1:1 UNITS: in.[mm]		REV. BY: KAL/TJD/MP




Figure 24. Hardware, Test No. MWP-9

Item No.	QTY.	Description	Material Specification	Galv. Specification
a1	2	Cable Anchor Base Plate	ASTM A36	AASHTO M111 (ASTM A123)
a2	4	Exterior Cable Plate Gusset	ASTM A36	AASHTO M111 (ASTM A123)
a3	6	Interior Cable Plate Gusset	ASTM A36	AASHTO M111 (ASTM A123)
a4	2	Anchor Bracket Plate	ASTM A36	AASHTO M111 (ASTM A123)
a5	2	3/16" [5] Dia. Brass Keeper Rod, 16 1/4" [413] Long Unbent	ASTM B16-00	-
a6	4	Release Gusset	A36 Steel	AASHTO M111 (ASTM A123)
a7	2	Release Lever Plate	A36 Steel	AASHTO M111 (ASTM A123)
a8	4	1 1/4x1 1/4x3/16" [32x32x5] TS CT Kicker Lever Tube	ASTM A500 Gr. B	AASHTO M111 (ASTM A123)
a9	8	CMB High Tension Anchor Plate Washer	ASTM A36	AASHTO M111 (ASTM A123)
a10	2	1 1/4x1 1/4x3/16" [32x32x5] TS CT Kicker Lever Connecting Tube	ASTM A500 Gr. B	AASHTO M111 (ASTM A123)
a11	2	3 1/2"x13 1/2"x1/2" [89x343x13] Kicker Plate	ASTM A36	AASHTO M111 (ASTM A123)
a12	4	CT Kicker - Gusset	ASTM A36	AASHTO M111 (ASTM A123)
a13	20	3/4" [19] Dia. Flat Washer	ASTM F844	AASHTO M232 (ASTM A153) for Class C or AASHTO M298 (ASTM B695) for Class 50
a14	16	3/4" [19] Dia. UNC J-Hook Anchor	ASTM A449 Type 1	AASHTO M232 (ASTM A153) for Class C or AASHTO M298 (ASTM B695) for Class 50
a15	2	1/4" [6] Dia. 7x19 Aircraft Retaining Cable, 36" [914] Long	ASTM A1023	ASTM A1007
a16	2	5/8" [16] Dia. Heavy Hex Nut	ASTM A563C	AASHTO M232 (ASTM A153) for Class C or AASHTO M298 (ASTM B695) for Class 50
a17	2	5/8" [16] Dia. UNC, 9 1/2" [241] Long Hex Bolt	ASTM A449 Type 1 or SAE J429 Gr. 5	AASHTO M232 (ASTM A153) for Class C or AASHTO M298 (ASTM B695) for Class 50
a18	2	24" [610] Dia. Concrete Anchor, 120" [3048] Long	Min. f'c = 4,000 psi [27.6 MPa]	-
a19	16	#11 Straight Rebar, 114" [2896] Long	ASTM A615 Gr. 60 or ASTM A706 Gr. 60	-
a20	44	#4 Anchor Hoop Rebar with 21" [533] Dia., 84" [2134] Long Unbent	ASTM A615 Gr. 60 or ASTM A706 Gr. 60	-
a21	18	3/4" [19] Dia. UNC Heavy Hex Nut	ASTM A563DH	AASHTO M232 (ASTM A153) for Class C or AASHTO M298 (ASTM B695) for Class 50
b1	2	S3x5.7 [S76x8.5] Post, 28 1/8" [714] Long	ASTM A572 GR50-07, ASTM A709 GR50-09A, ASTM A992-06A	AASHTO M111 (ASTM A123)
b2	2	S3x5.7 [S76x8.5] Post, 19" [483] Long	ASTM A572 GR50-07, ASTM A709 GR50-09A, ASTM A992-06A	AASHTO M111 (ASTM A123)
b3	8	#3 Straight Rebar, 43" [1092] Long	ASTM A615 Gr. 60 or ASTM A706 Gr. 60	-
b4	22	7 1/4" [184] Dia. No. 3 Hoop Reinforcement, 37" [940] Long Unbent	ASTM A615 Gr. 60 or ASTM A706 Gr. 60	-
b5	2	2nd Post Keeper Plate, 28 Gauge	ASTM A36	AASHTO M111 (ASTM A123)


 Midwest Roadside Safety Facility	Midwest 4-Cable Barrier System	SHEET: 25 of 26
	Bill of Materials	DATE: 1/26/2018
DWG. NAME: MWP-9_R6	SCALE: NONE	DRAWN BY: JEK
UNIT: in.[mm]	REV. BY: KAL/LJD/MP	

Figure 25. Bill of Materials, Test No. MWP-9

Item No.	QTY.	Description	Material Specification	Galv. Specification
b6	2	3/4" [19] Dia. UNC, 5 1/2" [140] Long Hex Bolt and Nut	Bolt ASTM A307 Gr. A/Nut ASTM A563A	AASHTO M232 (ASTM A153) for Class C or AASHTO M298 (ASTM B695) for Class 50
b7	24	1/2" [13] Dia. Washer with 1 1/16" [27] OD	ASTM F844	AASHTO M232 (ASTM A153) for Class D or AASHTO M298 (ASTM B695) for Class 50
b8	8	1/2" [13] Dia. UNC, 2" [51] Long Hex Bolt and Nut	Bolt ASTM A307 Gr. A/Nut ASTM A563A	AASHTO M232 (ASTM A153) for Class C or AASHTO M298 (ASTM B695) for Class 50
b9	2	4x3x1/4" [102x76x6] Foundation Tube, 48" [1219] Long	ASTM A500 Grade B	AASHTO M111 (ASTM A123)
b10	2	2nd Post Cable Hanger	ASTM A36	AASHTO M111 (ASTM A123)
b11	2	12" [305] Dia. 2nd Post Anchor Aggregate, 2" [51] Deep	Standard Strong Soil	-
b12	2	12" [305] Dia. 2nd Post Concrete Anchor, 46" [1168] Long	Min f'c = 4,000 psi [27.6 MPa]	-
b13	4	2nd Post Base Plate	ASTM A36	AASHTO M111 (ASTM A123)
b14	8	3/16" [5] Dia., 5 1/8" [130] Long Unbent Brass Rod	ASTM B16-00	-
c1	72	3"x1-3/4"x7 Gauge [76x44x4.6] x 79 5/8" [2022] Long Bent Z-Section Post with 3/4" [19] Dia. Weakening Holes	Hot-Rolled ASTM A1011 HSLA Gr. 50	AASHTO M111 (ASTM A123)
c2	216	12 Gauge Tabbed Bracket - Version 10	Hot-Rolled ASTM A1011 HSLA Gr. 50	AASHTO M111 (ASTM A123)
c3	216	5/16" [8] Dia. UNC, 1" [25] Long Hex Cap Screw and Nut	Bolt SAE J429 Gr. 5 or ASTM A449 Type 1/Nut ASTM A563DH	AASHTO M232 (ASTM A153) for Class C or AASHTO M298 (ASTM B695) for Class 50
c4	72	1/2" [13] Dia. UNC, 4" [102] Long Hex Bolt and Nut	Bolt SAE J429 Gr. 5 or ASTM A449 or ASTM A325/Nut ASTM A563DH	AASHTO M232 (ASTM A153) for Class C or AASHTO M298 (ASTM B695) for Class 50
c5	72	2 1/8"x1 3/8"x7 Gauge [54x35x4.6], 6" [152] Long Bent Steel Plate	Hot-Rolled ASTM A1011 HSLA Gr. 50	AASHTO M111 (ASTM A123)
c6	72	2 1/8"x1 3/8"x7 Gauge [54x35x4.6], 6" [152] Long Bent Steel Plate	Hot-Rolled ASTM A1011 HSLA Gr. 50	AASHTO M111 (ASTM A123)
c7	72	3/16" [5] Dia. Brass Cable Clip, 4 9/16" [116] Long Unbent	ASTM B16 Brass C36000 Half Hard (H02), ROUND, TS >= 68.0 ksi, YS >= 52.0 ksi	-
d1	1	3/4" [19] Dia. 3x7 Cable Guiderail	AASHTO M30 Type 1 or ASTM A741 Type 1 with minimum breaking strength = 39 kips (173.5 kN)	Class A
d2	16	7/8" [22] Dia. Heavy Hex Nut	ASTM A563C	AASHTO M232 (ASTM A153) for Class C or AASHTO M298 (ASTM B695) for Class 50
d3	28	7/8" [22] Dia. UNC, 11" [279] Long Threaded Rod	ASTM A449 Type 1 or ASTM A193 Gr. B7	AASHTO M232 (ASTM A153) for Class C or AASHTO M298 (ASTM B695) for Class 50
d4	24	Bennett Cable End Fitter	ASTM A47	AASHTO M232 (ASTM A153) for Class A
d5	24	7/8" [22] Dia. Hex Nut	ASTM A563DH	AASHTO M232 (ASTM A153) for Class C or AASHTO M298 (ASTM B695) for Class 50
e1	8	Bennett Short Threaded Turnbuckle	As Supplied	-
e2	8	Threaded Load Cell Coupler	Not Applicable (NA)	NA
e3	4	50,000-lb [222.4-kN] Load Cell	Not Applicable (NA)	NA


 Midwest Roadside Safety Facility	Midwest 4-Cable Barrier System	SHEET: 26 of 26
	Bill of Materials	DATE: 1/26/2018
DWG. NAME: MWP-9_r6	SCALE: NONE UNITS: in./mm	DRAWN BY: JEK REV. BY: KAL/TJD/ MB

Figure 26. Bill of Materials, Test No. MWP-9



Figure 27. System Installation, Test No. MWP-9



Figure 28. Post and Cap Details, Test No. MWP-9



Figure 29. Bracket Details, Test No. MWP-9



Figure 30. Upstream Cable Splices, Test No. MWP-9



Figure 31. Downstream Cable Splices, Test No. MWP-9



Figure 32. Upstream Anchorage, Test No. MWP-9



Figure 33. Downstream Anchorage, Test No. MWP-9

4 TEST CONDITIONS

4.1 Test Facility

The outdoor test site is located at the Lincoln Air Park on the northwest side of the Lincoln Municipal Airport and is approximately 5 miles (8.0 km) northwest of the University of Nebraska-Lincoln.

4.2 Vehicle Tow and Guidance System

A reverse-cable, tow system with a 1:2 mechanical advantage was used to propel the test vehicle. The distance traveled and the speed of the tow vehicle were one-half that of the test vehicle. The test vehicle was released from the tow cable before impact with the barrier system. A digital speedometer on the tow vehicle increased the accuracy of the test vehicle impact speed.

A vehicle guidance system developed by Hinch [8] was used to steer the test vehicle. A guide flag, attached to the right-front wheel and the guide cable, was sheared off before impact with the barrier system. The $\frac{3}{8}$ -in. (9.5-mm) diameter guide cable was tensioned to approximately 3,500 lb (15.6 kN) and supported both laterally and vertically every 100 ft (30.5 m) by hinged stanchions. The hinged stanchions stood upright while holding up the guide cable, but as the vehicle was towed down the line, the guide flag struck and knocked each stanchion to the ground.

4.3 Test Vehicle

For test no. MWP-9, a 2008 Kia Rio was used as the test vehicle. The curb, test inertial, and gross static vehicle weights were 2,457 lb (1,114 kg), 2,421 lb (1,098 kg), and 2,594 lb (1,177 kg), respectively. The test vehicle is shown in Figures 34 and 35, and vehicle dimensions are shown in Figure 36. Note that pre-test photographs of the vehicle's undercarriage are not available.

The longitudinal component of the center of gravity (c.g.) was determined using the measured axle weights. The vertical component of the c.g. for the 1100C vehicle was determined utilizing a procedure published by SAE [9]. The location of the final c.g. is shown in Figures 36 and 37. Data used to calculate the location of the c.g. and ballast information is shown in Appendix B.

Square, black- and white-checked targets were placed on the vehicle for reference to be viewed from the high-speed digital video cameras and aid in the video analysis, as shown in Figure 37. Round, checkered targets were placed at the c.g. on the left-side door, the right-side door, and the roof of the vehicle.

The front wheels of the test vehicle were aligned to vehicle standards except the toe-in value was adjusted to zero so that the vehicle would track properly along the guide cable. A 5B flash bulb was mounted under the vehicle's left-side windshield wiper and was fired by a pressure tape switch mounted at the impact corner of the bumper. The flash bulb was fired upon initial impact with the test article to create a visual indicator of the precise time of impact on the high-speed digital videos. A remote-controlled brake system was installed in the test vehicle so the vehicle could be brought safely to a stop after the test.




Figure 34. Test Vehicle, Test No. MWP-9



Figure 35. Test Vehicle's Interior Floorboards, Test No. MWP-9

Date: 10/31/2016 Test Number: MWP-9 Model: Rio
Make: Kia Vehicle I.D.#: KNADE123086347849
Tire Size: 185/65R14 86T Year: 2008 Odometer: 89814
Tire Inflation Pressure: 32
*(All Measurements Refer to Impacting Side)



Vehicle Geometry -- in. (mm)

a	<u>64 7/8 (1648)</u>	b	<u>58 3/8 (1483)</u>
c	<u>166 7/8 (4239)</u>	d	<u>36 1/4 (921)</u>
e	<u>98 1/2 (2502)</u>	f	<u>33 1/8 (841)</u>
g	<u>23 1/8 (587)</u>	h	<u>36 1/2 (927)</u>
i	<u>9 1/8 (232)</u>	j	<u>21 1/4 (540)</u>
k	<u>16 1/4 (413)</u>	l	<u>25 (635)</u>
m	<u>57 (1448)</u>	n	<u>57 1/8 (1451)</u>
o	<u>30 3/8 (772)</u>	p	<u>4 1/8 (105)</u>
q	<u>23 1/2 (597)</u>	r	<u>15 3/8 (391)</u>
s	<u>7 7/8 (200)</u>	t	<u>65 (1651)</u>

Wheel Center Height Front 10 3/4 (273)
Wheel Center Height Rear 11 1/4 (286)
Wheel Well Clearance (F) 25 1/4 (641)
Wheel Well Clearance (R) 25 3/8 (645)
Frame Height (F) 6 1/4 (159)
Frame Height (R) 16 3/8 (416)
Engine Type Gasoline
Engine Size 1.6 L
Transmission Type: Automatic
Drive Axle: Front

Mass Distribution lb (kg)

Gross Static	LF <u>826 (375)</u>	RF <u>790 (358)</u>
	LR <u>494 (224)</u>	RR <u>484 (220)</u>

Weights lb (kg)

	Curb	Test Inertial	Gross Static
W-front	<u>1568 (711)</u>	<u>1525 (692)</u>	<u>1616 (733)</u>
W-rear	<u>889 (403)</u>	<u>896 (406)</u>	<u>978 (444)</u>
W-total	<u>2457 (1114)</u>	<u>2421 (1098)</u>	<u>2594 (1177)</u>

GVWR Ratings

Front	<u>1918</u>
Rear	<u>1874</u>
Total	<u>3638</u>

Dummy Data

Type: Hybrid II
Mass: 173 lb
Seat Position: Driver

Note any damage prior to test: Extensive Hail Damage

Figure 36. Vehicle Dimensions, Test No. MWP-9




Figure 37. Target Geometry, Test No. MWP-9

4.4 Simulated Occupant

For test no MWP-9, a Hybrid II 50th-Percentile, Adult Male Dummy, equipped with clothing and footwear, was placed in the left-front seat of the test vehicle with the seat belt fastened. The dummy, which had a final weight of 173 lb (78 kg), was represented by model no. 572, serial no. 451, and was manufactured by Android Systems of Carson, California. As recommended by MASH 2016, the dummy was not included in calculating the c.g. location.

4.5 Data Acquisition Systems

4.5.1 Accelerometers

Two environmental, shock and vibration, sensor/recorder systems were used to measure the accelerations in the longitudinal, lateral, and vertical directions. Both accelerometer systems were mounted near the c.g. of the test vehicle. The electronic accelerometer data obtained in dynamic testing was filtered using the SAE Class 60 and the SAE Class 180 Butterworth filter conforming to the SAE J211/1 specifications [10].

The two accelerometer systems, the SLICE-1 and SLICE-2 units, were modular data acquisition systems manufactured by Diversified Technical Systems, Inc. (DTS) of Seal Beach, California. The SLICE-1 unit was designated as the primary system. The acceleration sensors were mounted inside the bodies of custom-built, SLICE 6DX event data recorders and recorded data at 10,000 Hz to the onboard microprocessor. Each SLICE 6DX was configured with 7 GB of non-volatile flash memory, a range of ± 500 g's, a sample rate of 10,000 Hz, and a 1,650 Hz (CFC 1000) anti-aliasing filter. The "SLICEWare" computer software program and a customized Microsoft Excel worksheet were used to analyze and plot the accelerometer data.

4.5.2 Rate Transducers

Two identical angular rate sensor systems mounted inside the bodies of the SLICE-1 and SLICE-2 event data recorders were used to measure the rates of rotation of the test vehicle. Each SLICE MICRO Triax ARS had a range of 1,500 degrees/sec in each of the three directions (roll, pitch, and yaw) and recorded data at 10,000 Hz to the onboard microprocessors. The raw data measurements were then downloaded, converted to the proper Euler angles for analysis, and plotted. The "SLICEWare" computer software program and a customized Microsoft Excel worksheet were used to analyze and plot the angular rate sensor data.

4.5.3 Retroreflective Optic Speed Trap

The retroreflective optic speed trap was used to determine the speed of the test vehicle before impact. Five retroreflective targets, spaced at approximately 18-in. (457-mm) intervals, were applied to the side of the vehicle. When the emitted beam of light was reflected by the targets and returned to the Emitter/Receiver, a signal was sent to the data acquisition computer, recording at 10,000 Hz, as well as the external LED box activating the LED flashes. The speed was then calculated using the spacing between the retroreflective targets and the time between the signals. LED lights and high-speed digital video analysis are only used as a backup in the event that vehicle speeds cannot be determined from the electronic data.

4.5.4 Load Cells and String Potentiometers

Four load cells were installed upstream of the impact between post nos. 6 and 7 (cable nos. 2 and 4) and between post nos. 7 and 8 (cable nos. 1 and 3). The load cells were Transducer Techniques model no. TLL-50K with a load range up to 50 kips (222 kN). A string potentiometer was also attached to the system on the upstream anchor. The string potentiometer was Unimeasure model no. PA-50-70124 with a displacement range up to 50 in. (127 cm). During testing, output voltage signals were sent from the transducers to a National Instruments PCI-6071E data acquisition board, acquired with LabView software, and stored on a personal computer at a sample rate of 10,000 Hz. The positioning and set up of the transducers are shown in Figure 38.


4.5.5 Digital Photography

Six AOS high-speed digital video cameras, eleven GoPro digital video cameras, and three JVC digital video cameras were utilized to film test no. MWP-9. Camera details, camera operating speeds, lens information, and a schematic of the camera locations relative to the system are shown in Figure 39.

The high-speed digital videos were analyzed using ImageExpress MotionPlus, TEMA Motion, and RedLake MotionScope software programs. Actual camera speed and camera divergence factors were considered in the analysis of the high-speed videos. A Nikon digital still camera was also used to document pre- and post-test conditions for all tests.



Figure 38. Location of Load Cells and String Potentiometers, Test No. MWP-9



No.	Type	Operating Speed (frames/sec)	Lens	Lens Setting
AOS-2	AOS Vitcam CTM	500	Kowa 25mm Fixed	--
AOS-5	AOS X-PRI Gigabit	500	Telesar 135mm Fixed	--
AOS-6	AOS X-PRI Gigabit	500	Sigma 28-70 DG	35
AOS-7	AOS X-PRI Gigabit	500	Sigma 28-70	50
AOS-8	AOS S-VIT 1531	500	Kowa 16mm Fixed	--
AOS-9	AOS TRI-VIT	1000	Kowa 12mm Fixed	--
GP-3	GoPro Hero 3+	120		
GP-4	GoPro Hero 3+	120		
GP-5	GoPro Hero 3+	120		
GP-6	GoPro Hero 3+	120		
GP-7	GoPro Hero 4	240		
GP-8	GoPro Hero 4	240		
GP-9	GoPro Hero 4	120		
GP-10	GoPro Hero 4	240		
GP-12	GoPro Hero 4	120		
GP-13	GoPro Hero 4	120		
GP-14	GoPro Hero 4	120		
JVC-2	JVC - GZ-MG27u (Everio)	29.97		
JVC-3	JVC - GZ-MG27u (Everio)	29.97		
JVC-4	JVC - GZ-MG27u (Everio)	29.97		

Figure 39. Camera Locations, Speeds, and Lens Settings, Test No. MWP-9

5 FULL-SCALE CRASH TEST NO. MWP-9

5.1 Static Soil Test

Before full-scale crash test no. MWP-9 was conducted, the strength of the foundation soil was evaluated with a static test, as described in MASH 2016. The static test results, as shown in Appendix C, demonstrated a soil resistance above the baseline test limits. Thus, the soil provided adequate strength, and full-scale crash testing could be conducted on the barrier system.

5.2 Weather Conditions

Test no. MWP-9 was conducted on October 31, 2016 at approximately 3:15 p.m. The weather conditions as per the National Oceanic and Atmospheric Administration (station 14939/LNK) were reported and are shown in Table 3.

Table 3. Weather Conditions, Test No. MWP-9

Temperature	71° F
Humidity	61%
Wind Speed	14 mph
Wind Direction	190° from True North
Sky Conditions	Partly Cloudy
Visibility	10 Statute Miles
Pavement Surface	Dry
Previous 3-Day Precipitation	0.00 in.
Previous 7-Day Precipitation	0.01 in.

5.3 Test Description

The 2,421-lb (1,098-kg) car impacted the cable barrier system at a speed of 63.1 mph (101.5 km/h) and at an angle of 25.7 degrees. A summary of the test results and sequential photographs are shown in Figure 42. Additional sequential photographs are shown in Figures 43 through 45.

Initial vehicle impact was to occur at a midspan location, or 4 ft (1.22 m) upstream from post no. 31, as shown in Figure 46, which was selected using Table 2-2D of MASH 2016. The actual point of impact was 3 ft – 10 in. (1.17 m) upstream of post no. 31. A sequential description of the impact events is contained in Table 4. The vehicle came to rest approximately 150 ft – 2 in. (45.77 m) downstream from the point of impact, or between post nos. 48 and 49 and in contact with the cables. Cable no. 4 was located on the non-impact side of the vehicle, cable no. 2 was located on the impact side, and cable nos. 1 and 3 were underneath the vehicle. The vehicle trajectory and final position are shown in Figures 47 and 48.

Table 4. Sequential Description of Impact Events, Test No. MWP-9

TIME (sec)	EVENT
0.000	Vehicle's left-front bumper contacted cable no. 2.
0.002	Vehicle's left-front bumper contacted cable no. 1.
0.012	Vehicle's left fender contacted cable no. 3.
0.024	Cable no. 3 disengaged from post no. 31.
0.026	Post no. 31 bent downstream.
0.028	Cable no. 4 disengaged from post no. 31.
0.032	Cable no. 1 disengaged from post no. 31.
0.034	Cable no. 3 disengaged from post no. 30, cable no. 2 disengaged from post no 31.
0.038	Post no. 31 bent backward.
0.042	Cable no. 3 disengaged from post no. 32.
0.046	Post no. 32 bent backward, the vehicle's left-side mirror deformed.
0.050	Vehicle's left A-pillar contacted cable no. 3, post no. 30 deflected backward.
0.056	Cable no. 3 disengaged from post no. 29, vehicle's left-front tire overrode cable no. 1.
0.064	Vehicle's left A-pillar contacted cable no. 4, left-front tire overrode post no. 31, post no. 30 deflected upstream.
0.066	Cable no. 3 disengaged from post no. 33.
0.069	Post no. 33 deflected backward.
0.072	Vehicle's left-fender contacted cable no. 2.
0.084	Vehicle's left-side mirror disengaged, cable no. 3 disengaged from post no. 34, vehicle's left-front tire regained contact with ground.
0.092	Vehicle's hood deformed, cable no. 3 contacted windshield.
0.098	Cable no. 4 contacted vehicle's windshield and disengaged from post no. 32.
0.102	Post no. 30 bent backward, vehicle's front bumper contacted post no. 32, and vehicle's left-front door contacted cable no. 2.
0.104	Post no. 33 bent backward, cable no. 2 disengaged from post no. 32.
0.110	Vehicle yawed away from barrier, post no. 32 bent downstream.
0.120	Vehicle's left A-pillar deformed, cable no. 2 disengaged from post no. 33.
0.132	Vehicle rolled away from barrier, cable no. 4 disengaged from post no. 33.
0.138	Post no. 34 bent backward.
0.150	Cable no. 4 disengaged from post no. 34, vehicle pitched upward, cable no. 4 disengaged from post no. 30.
0.160	Vehicle's left-rear tire overrode cable no. 1.
0.166	Vehicle's windshield shattered from contact with cable nos. 1 and 2, cable no. 4 disengaged from post no. 35.
0.174	Vehicle's left-front window shattered from contact with cable nos. 1 and 2.
0.176	Cable no. 4 disengaged from post no. 29.

0.193	Post no. 35 deflected backward, cable no. 3 contacted vehicle's left B-pillar.
0.202	Cable no. 4 contacted vehicle's left B-pillar.
0.208	Vehicle's right-side headlight deformed, cable no. 4 disengaged from post no. 37, vehicle's right-front tire overrode cable no. 1.
0.210	Vehicle's left-front tire became airborne, right-side headlight contacted post no. 33, post no. 36 deflected backward, cable no. 2 disengaged from post no. 34.
0.224	Post no. 35 bent backward, cable no. 3 disengaged from post no. 35.
0.234	Cable no. 1 disengaged from post no. 33.
0.238	Post no. 36 bent backward.
0.240	Cable no. 2 disengaged from post no. 35, cable no. 3 disengaged from post no. 36.
0.249	Post no. 37 deflected backward, cable no. 4 disengaged from post no. 38.
0.262	Cable no. 3 disengaged from post no. 37, vehicle pitched downward.
0.266	Cable no. 4 disengaged from post no. 39, post no. 37 bent backward.
0.282	Post no. 38 deflected backward.
0.286	Cable no. 2 disengaged from post no. 36.
0.292	Cable no. 4 disengaged from post no. 40.
0.312	Cable no. 2 disengaged from post no. 37, post no. 35 deflected downstream, vehicle's left-front tire regained contact with ground.
0.336	Cable no. 3 contacted vehicle's left C-pillar.
0.356	Cable no. 4 contacted vehicle's left C-pillar.
0.360	Cable no. 3 disengaged from post no. 38.
0.365	Vehicle's right-side mirror contacted post no. 34 and disengaged.
0.388	Cable no. 2 disengaged from post no. 38.
0.404	Post no. 39 deflected backward.
0.430	Vehicle pitched upward, cable no. 2 disengaged from post no. 30.
0.436	Cable no. 4 disengaged from post no. 41, post no. 39 rotated backward.
0.454	Cable no. 1 disengaged from post no. 30, vehicle rolled away from barrier.
0.504	Cable no. 2 disengaged from post no. 39.
0.542	Vehicle's right-rear door contacted post no. 35.
0.565	Vehicle's hood and right fender contacted post no. 36.
0.574	Post no. 36 bent downstream.
0.590	Cable nos. 3 and 4 contacted vehicle's roof.
0.596	Vehicle became parallel to system at a speed of 45.4 mph (73.1 km/h)
0.622	Vehicle rolled toward barrier.
0.658	Vehicle underrode cable nos. 3 and 4.
0.678	Post no. 37 bent downstream, cable no. 3 disengaged from post no. 39.
0.712	Cable no. 3 disengaged from post no. 40.
0.734	Cable no. 3 disengaged from post no. 41.
0.802	Cable no. 1 disengaged from post no. 38.

0.824	Post no. 38 bent downstream.
0.832	Cable no. 1 disengaged from post no. 39, right-front tire overrode cable no. 1.
0.920	Vehicle rolled away from barrier.
0.928	Vehicle's front bumper contacted post no. 39.
0.944	Cable no. 4 contacted vehicle's right fender.
0.966	Cable no. 4 contacted vehicle right A-pillar.
0.972	Post no. 39 bent downstream.
1.144	Vehicle's left tire and fender contacted post no. 40.
1.162	Post no. 40 bent downstream, cable no. 2 disengaged from post no. 40.
1.214	Vehicle's right-front tire overrode cable no. 3.
1.297	Vehicle's left-front fender contacted post no. 41.
1.674	Vehicle's left-front tire contacted cable no. 3.
1.870	Vehicle's left-front fender contacted post no. 44.
2.150	Post no. 45 deflected backward.
2.356	Vehicle's left-front fender contacted post no. 46, which deflected downstream.
2.958	Vehicle's left-front fender contacted post no. 47, which deflected downstream.
3.439	Vehicle's left-front fender contacted post no. 48, which deflected downstream.
4.331	Vehicle came to rest in system.

5.4 Barrier Damage

Damage to the barrier was moderate, as shown in Figures 49 through 85. Barrier damage consisted of bent posts, disengaged cables, and deformed brackets. At its final resting position, the vehicle was still in contact with the cables. Cable nos. 1 and 3 were underneath the vehicle while cable no. 4 was on the non-impact side of the vehicle and cable no. 2 was on the impact side of the vehicle. The length of vehicle contact along the barrier was approximately 150 ft – 2 in. (45.77 m), which spanned from 3 ft – 10 in. (1.17 m) upstream of post no. 31 to between post nos. 48 and 49. The release mechanism of each cable from the posts is summarized in Table 5.

Post nos. 27 through 40, 45 through 49, and 51 had varying degrees of plastic deformation in the form of bending and twisting. Typically, the posts were bent laterally backward and longitudinally downstream. Post nos. 30 through 36, 38 through 40, 42 through 45, and 48 through 51 encountered contact marks and grinding marks on the edges due to vehicle override. The vehicle came to a complete stop on top of post nos. 48 and 49.

The working width of the system was found to be 103.2 in. (2,621 mm), as determined from high-speed digital video analysis. The maximum lateral dynamic barrier deflection was 96.4 in. (2,449 mm), as determined from high-speed digital video analysis. The permanent set deflection of the barrier was 33¾ in. (857 mm), as measured in the field. The upstream anchor experienced a dynamic deflection of 0.3 in. (7 mm).

Table 5. Disengaged Cables and Release Mechanisms, Test No. MWP-9

Post No.	Cable No.			
	1	2	3	4
22	0	0	2	7
23	0	0	0	2
24	0	0	0	2
25	0	0	0	2
26	0	0	0	2
27	2	0	2	2
28	2	0	2	2
29	2	0	2	2
30	2	2	2	2
31	2	2	2	2
32	2	2	2	2
33	2	2	2	2
34	1	2	2	2
35	1	2	2	2
36	2	2	2	2
37	2	2	2	2
38	4	2	2	2
39	3	2	2	2
40	2	2	2	2
41	0	0	2	2
42	0	0	2	2
43	1	0	2	2
44	1	2	2	2
45	1	2	2	2
46	1	2	2	2
47	1	2	2	2
48	2	2	2	2
49	1	2	2	2
50	0	0	2	2
51	0	0	2	2
52	0	0	0	7

0- No Interaction 1- Deformed in Place 2- Released Entirely 3- Fractured at Tab
4- Fractured at Neck 5- Fractured through Bolt Hole 6- Brass Rod Fractured 7- Brass Rod Bent in Place

5.5 Vehicle Damage

The damage to the vehicle was moderate, as shown in Figures 86 through 88. The maximum occupant compartment deformations are listed in Table 6 along with the deformation limits established in MASH 2016 for various areas of the occupant compartment. Complete occupant compartment and vehicle deformations as well as the corresponding locations are provided in Appendix D.

Table 6. Maximum Occupant Compartment Deformations by Location

LOCATION	MAXIMUM DEFORMATION in. (mm)	MASH 2016 ALLOWABLE DEFORMATION in. (mm)
Wheel Well & Toe Pan	$\frac{3}{8}$ (10)	≤ 9 (229)
Floor Pan & Transmission Tunnel	$\frac{1}{4}$ (6)	≤ 12 (305)
A- and B-Pillars	3.9 (99)	≤ 5 (127)
A- and B-Pillars (Lateral)	3.4 (86)	≤ 3 (76)
Side Front Panel (in Front of A-Pillar)	$\frac{1}{4}$ (6)	≤ 12 (305)
Side Door (Above Seat)	$\frac{1}{2}$ (13)	≤ 9 (229)
Side Door (Below Seat)	$\frac{1}{4}$ (6)	≤ 12 (305)
Roof	$1\frac{7}{8}$ (48)	≤ 4 (102)
Windshield	$\frac{1}{4}$ (6)	≤ 3 (76)
Side Window	Shattered due to contact with cable	No shattering as a result of direct contact with structural member of test article (acceptable if shatters due to contact with cable when A-pillar deformation ≤ 3 (76))
Dash	$\frac{1}{2}$ (13)	N/A

N/A – Not Applicable

The majority of the vehicle damage was concentrated on the left-front corner, where primary impact occurred, and on the right-front corner, where the vehicle redirected back into the system. The cables caused striation marks, scrapes, and gouges along the left-front and right-front fenders and up the entire length of the A-pillar, B-pillar, and C-pillar on the left side of the vehicle. As the vehicle overrode the system, cable no. 3 snagged on the cap retainer bolt and nut and induced an increased downward and lateral force to the A-pillar. Consequently, cable nos. 3 and 4 became interlocked with the A-pillar on the impact side, resulting in an excessive A-pillar crush of 3.4 in. (86 mm), which is greater than the 3-in. (76-mm) MASH 2016 limit. Contact marks were also found on the roof, which were caused by the vehicle underriding cable nos. 3 and 4. The front bumper covers, both headlights, and both side mirrors disengaged from the vehicle. The left-front side window and windshield shattered on the left side of the vehicle near the A-pillar. The left-front rim had contact marks, and the right-front tire was deflated. Several scrapes and dents were observed along both frame rails of the vehicle undercarriage. However, no visible tearing or crush on the vehicle floor pan occurred.

5.6 Occupant Risk

The calculated occupant impact velocities (OIVs) and maximum 0.010-sec average occupant ridedown accelerations (ORAs) in both the longitudinal and lateral directions are shown in Table 7. Note that the OIVs and ORAs were within suggested limits, as provided in MASH 2016. The calculated THIV, PHD, and ASI values are also shown in Table 7. The results of the occupant risk analysis, as determined from the accelerometer data, are summarized in Figure 42. The recorded data from the accelerometers and the rate transducers are shown graphically in Appendix E.

Table 7. Summary of OIV, ORA, THIV, PHD, and ASI Values, Test No. MWP-9

Evaluation Criteria		Transducer		MASH Limits
		SLICE-1 (Primary)	SLICE-2	
OIV ft/s (m/s)	Longitudinal	-15.22 (-4.64)	-16.34 (-4.98)	± 40 (12.2)
	Lateral	13.07 (3.98)	12.53 (3.82)	± 40 (12.2)
ORA g's	Longitudinal	-5.53	-6.15	± 20.49
	Lateral	-7.26	-6.21	± 20.49
MAX ANGULAR DISPLACEMENT deg.	Roll	5.39	6.51	± 75
	Pitch	5.98	3.27	± 75
	Yaw	34.58	34.10	not required
THIV ft/s (m/s)		19.23 (5.86)	20.47 (6.24)	not required
PHD g's		7.61	8.47	not required
ASI		0.53	0.50	not required

5.7 Load Cells and String Potentiometer

The pertinent data from the load cells and string potentiometer was extracted from the bulk signal and analyzed using the transducers' calibration factors, as shown in Figures 40 and 41, respectively. The maximum displacement of the upstream anchor was recorded as 0.3 in. (7 mm). A summary of the maximum cable loads can be found Table 8. The recorded data and analyzed results are detailed in Appendix F. The exact moment of impact could not be determined from the transducer data as impact may have occurred a few milliseconds prior to observing a measurable signal in the electronic data. Thus, the extracted data curves should not be taken as a precise time after impact, but rather a general timeline between events within the data curve itself.

Table 8. Maximum Cable Loads, Test No. MWP-9

Cable Location	Sensor Location	Maximum Cable Load kips (kN)	Time (sec)
Combined Cable Load	Upstream of Impact	34.7 (154.4)	0.3364
Cable No. 4	Upstream of Impact between Post Nos. 6 and 7	8.9 (39.6)	1.2249
Cable No. 3	Upstream of Impact between Post Nos. 7 and 8	11.3 (50.3)	0.3786
Cable No. 2	Upstream of Impact between Post Nos. 6 and 7	14.6 (64.9)	0.2821
Cable No. 1	Upstream of Impact between Post Nos. 7 and 8	10.3 (45.8)	0.7823




Figure 40. Cable Tension Loads, Test No. MWP-9







Figure 41. Displacement of Upstream Anchor, Test No. MWP-9

5.8 Discussion

The analysis of the test results for test no. MWP-9 showed that the high-tension four-cable median barrier adequately contained and redirected the 1100C vehicle with controlled lateral displacements of the barrier. The test vehicle did not penetrate or ride over the barrier, and remained upright during and after the collision. Vehicle roll, pitch, and yaw angular displacements, as shown in Appendix E, were deemed acceptable because they did not adversely influence occupant risk safety criteria nor cause rollover. After impact, the vehicle was captured and retained within the system, thus it did not exit the system. As the vehicle passed across various system components, cable no. 3 snagged on the top cap retainer bolt and nut and induced an increased downward and lateral force to the left-side A-pillar. Consequently, cable nos. 3 and 4 became interlocked with the deformed A-pillar on the impact side, resulting in an excessive lateral A-pillar crush of 3.4 in. (86 mm), which is greater than the 3-in. (76-mm) lateral MASH 2016 limit. Additionally, the left-front side window shattered due to contact with cable nos. 1 and 2, which is unacceptable when the A- or B-pillar crush exceeds the MASH 2016 limit of 3 in. (76 mm). Tearing and penetration did not occur to the vehicle's floor pan. Thus, the two-part cap design that was used in test no. MWP-9 mitigated floor pan tearing and post penetration, but the test results were deemed unacceptable due to excessive A-pillar crush and the shattering of the left-front side window.



58

- Test AgencyMwRSF
- Test Number..... MWP-9
- Date 10/31/2016
- MASH Test Designation No.3-10
- Test Article.....Four-Cable Median Barrier
- Total Length..... 604 ft (184.1 m)
- Key Component – Cable
 - Size 3x7, 3/4-in. (19-mm) diameter
 - Cable Heights 15½, 23, 30½, 38 in. (394, 584, 775, 965 mm)
- Key Component – MWP
 - Dimensions..... 3 x 1¾ x 81¼ in. (76 x 44 x 2,064 mm)
 - Spacing 8 ft (2.44 m)
- Soil TypeCompacted, coarse, crushed limestone
- Vehicle Make /Model.....2008 Kia Rio
 - Curb.....2,457 lb (1,114 kg)
 - Test Inertial.....2,421 lb (1,098 kg)
 - Gross Static.....2,594 lb (1,177 kg)
- Impact Conditions
 - Speed63.1 mph (101.4 km/h)
 - Angle 25.7 deg
 - Impact Location..... 3 ft – 10 in. (1.17 m) upstream of Post No. 31
- Impact Severity 60.5 kip-ft (82.0 kJ) > 51 kip-ft (69.1 kJ) limit from MASH 2016
- Exit Conditions
 - Speed NA
 - Angle NA
- Exit Box Criterion NA (Did not exit system)
- Vehicle Stability..... Satisfactory
- Vehicle Stopping Distance 150 ft - 2 in. (45.77 m) Downstream within the system

- Vehicle Damage..... Moderate
 - VDS [11] 11-LFQ-5
 - CDC [12]..... 11-LYAK-9
 - Maximum Interior Deformation 3.4 in. (86 mm)
- Test Article Damage Moderate
- Maximum Test Article Deflections
 - Permanent Set 33¾ in. (857 mm)
 - Dynamic 96.4 in. (2,449 mm)
 - Working Width..... 103.2 in. (2,621 mm)
- Transducer Data

Evaluation Criteria		Transducer		MASH 2016 Limit
		SLICE-1 (primary)	SLICE-2	
OIV ft/s (m/s)	Longitudinal	-15.22 (-4.64)	-16.34 (-4.98)	± 40 (12.2)
	Lateral	13.07 (3.98)	12.53 (3.82)	± 40 (12.2)
ORA g's	Longitudinal	-5.53	-6.15	± 20.49
	Lateral	-7.26	-6.21	± 20.49
MAX ANGULAR DISPLACEMENT	Roll	5.39	6.51	±75
	Pitch	5.98	3.27	±75
	Yaw	34.58	34.10	not required
THIV – ft/s (m/s)		19.23 (5.86)	20.47 (6.24)	not required
PHD – g's		7.61	8.47	not required
ASI		0.53	0.50	not required

Figure 42. Summary of Test Results and Sequential Photographs, Test No. MWP-9



0.000 sec



0.109 sec



0.202 sec



0.286 sec



0.395 sec



0.479 sec



0.000 sec



0.502 sec



0.803 sec



1.406 sec



2.711 sec



4.017 sec

Figure 43. Sequential Photographs, Test No. MWP-9



0.000 sec



0.078 sec



0.210 sec




0.596 sec




0.946 sec




2.204 sec




0.000 sec




0.525 sec




1.475 sec



2.254 sec



2.966 sec



4.050 sec

Figure 44. Sequential Photographs, Test No. MWP-9



0.000 sec



0.143 sec



0.445 sec



0.647 sec



0.950 sec



1.655 sec



0.000 sec



0.525 sec



1.475 sec



2.254 sec



2.966 sec



4.050 sec

Figure 45. Additional Sequential Photographs, Test No. MWP-9




Figure 46. Impact Location, Test No. MWP-9




Figure 47. Vehicle Final Position, Test No. MWP-9



Figure 48. Vehicle Trajectory, Test No. MWP-9



Figure 49. System Damage, Test No. MWP-9



Post Nos. 21 through 23



Post Nos. 24 and 25



Post Nos. 26 and 27

Figure 50. Post Nos. 21 through 27 Damage, Test No. MWP-9



Post Nos. 28



Post Nos. 29 and 30



Post Nos. 31 through 33

Figure 51. Post Nos. 28 through 33 Damage, Test No. MWP-9



Post Nos. 34 and 35



Post Nos. 36 through 38



Post Nos. 40 through 43

Figure 52. Post Nos. 34 through 43 Damage, Test No. MWP-9



Post Nos. 44 through 46



Post Nos. 47 and 48



Post Nos. 49 through 51

Figure 53. Post Nos. 44 through 51 Damage, Test No. MWP-9



Figure 54. Post No. 22 Damage, Test No. MWP-9




Figure 55. Post No. 23 Damage, Test No. MWP-9




Figure 56. Post No. 24 Damage, Test No. MWP-9



Figure 57. Post No. 25 Damage, Test No. MWP-9



Figure 58. Post No. 26 Damage, Test No. MWP-9



Figure 59. Post No. 27 Damage, Test No. MWP-9




Figure 60. Post No. 28 Damage, Test No. MWP-9



Figure 61. Post No. 29 Damage, Test No. MWP-9




Figure 62. Post No. 30 Damage, Test No. MWP-9




Figure 63. Post No. 31 Damage, Test No. MWP-9



Figure 64. Post No. 32 Damage, Test No. MWP-9



Figure 65. Post No. 33 Damage, Test No. MWP-9




Figure 66. Post No. 34 Damage, Test No. MWP-9



Figure 67. Post No. 35 Damage, Test No. MWP-9



Figure 68. Post No. 36 Damage, Test No. MWP-9




Figure 69. Post No. 37 Damage, Test No. MWP-9



Figure 70. Post No. 38 Damage, Test No. MWP-9




Figure 71. Post No. 39 Damage, Test No. MWP-9



Figure 72. Post No. 40 Damage, Test No. MWP-9




Figure 73. Post No. 41 Damage, Test No. MWP-9



Figure 74. Post No. 42 Damage, Test No. MWP-9





Figure 75. Post No. 43 Damage, Test No. MWP-9



Figure 76. Post No. 44 Damage, Test No. MWP-9




Figure 77. Post No. 45 Damage, Test No. MWP-9




Figure 78. Post No. 46 Damage, Test No. MWP-9



Figure 79. Post No. 47 Damage, Test No. MWP-9



Figure 80. Post No. 48 Damage, Test No. MWP-9
96



Figure 81. Post No. 49 Damage, Test No. MWP-9




Figure 82. Post No. 50 Damage, Test No. MWP-9



Figure 83. Post No. 51 Damage, Test No. MWP-9
99



Post No. 52



Post No. 53

Figure 84. Post Nos. 52 and 53 Damage, Test No. MWP-9



Upstream Anchorage



Downstream Anchorage

Figure 85. Anchorage Damage, Test No. MWP-9



Figure 86. Vehicle Damage, Test No. MWP-9



Figure 87. Vehicle Damage, Test No. MWP-9



Figure 88. Vehicle Damage, Floor pan, Test No. MWP-9

6 SUMMARY AND CONCLUSIONS

The objective of this study was to continue to test and evaluate the prototype, high-tension, four-cable, median barrier system according to the MASH 2016 TL-3 safety criteria using the updated testing matrix for cable barrier systems installed within 6H:1V median V-ditches. One full-scale test was conducted on the system and is reported herein.

Test no. MWP-9, conducted in accordance with MASH 2016 test designation no. 3-10, involved an 1100C small car impacting the four-cable median barrier system with 8-ft (2.4-m) post spacing on level terrain. A summary of the test evaluation is shown in Table 9. Test MWP-9 utilized modified MWP with $\frac{3}{4}$ -in. (19-mm) diameter weakening holes at the ground line. The weakening holes reduced the post's weak-axis bending capacity to lower the contact forces between the post and the floor pan. Additionally, test no. MWP-9 contained a two-part cap at the top of the MWP to shield the free edges during post-to-undercarriage contact. During test no. MWP-9, the 2,421-lb (1,098-kg) car impacted the four-cable median barrier at a speed of 63.1 mph (101.5 km/h) and at an angle of 25.7 degrees, which resulted in an impact severity of 60.5 kip-ft (82.0 kJ).

Analysis of the test results showed that the system adequately contained and redirected the 1100C vehicle with controlled lateral displacements of the barrier. There were no detached elements or fragments that showed potential for penetrating the occupant compartment or presented undue hazard to other traffic. The test vehicle did not penetrate nor ride over the barrier and remained upright during and after the collision. Vehicle roll, pitch, and yaw angular displacements, as shown in Appendix E, were deemed acceptable because they did not adversely influence occupant risk safety criteria nor cause rollover. However, cable no. 3 snagged on the top cap retainer bolt and nut and induced an increased downward and lateral force to the vehicle's A-pillar. This action caused cable nos. 3 and 4 to become interlocked with the A-pillar on the impact side of the vehicle, resulting in excessive lateral A-pillar crush of 3.4 in. (86 mm), which is greater than the 3-in. (76-mm) lateral MASH 2016 limit. Additionally, the left-front side window shattered due to contact with cable nos. 1 and 2, which is unacceptable when the A- or B-pillar crush exceeds the MASH 2016 limit of 3 in. (76 mm). Tearing and penetration did not occur to the vehicle's floor pan. Thus, the two-part cap designed for this test was able to mitigate the floor pan tearing and post penetration into the occupant compartment, but the test was ultimately deemed unsuccessful due to excessive A-pillar crush and the shattering of the left-front side window.

As a result of the unsuccessful 1100C crash test, the prototype, high-tension, four-cable, median barrier system will need to be further redesigned to prevent the excessive A-pillar crush observed in test no. MWP-9. Possible design changes may include, but are not limited to, the use of closed-section posts, reduction of weak-axis bending strength at groundline, alternative treatment of post edges, and changes to post geometry. After the cable barrier system has been redesigned, it will need to be re-evaluated according to MASH 2016 test designation no. 3-10 criteria before proceeding with the remaining tests listed within the recommended testing matrix for cable barriers installed within median V-ditches. Depending on the nature of the design changes, it may be necessary to evaluate whether prior successful crash tests need to be rerun.

Table 9. Summary of Safety Performance Evaluation, Test No. MWP-9

Evaluation Factors	Evaluation Criteria	Test No. MWP-9	
Structural Adequacy	A. Test article should contain and redirect the vehicle or bring the vehicle to a controlled stop; the vehicle should not penetrate, underride, or override the installation although controlled lateral deflection of the test article is acceptable.	S	
Occupant Risk	D. 1. Detached elements, fragments or other debris from the test article should not penetrate or show potential for penetrating the occupant compartment, or present an undue hazard to other traffic, pedestrians, or personnel in a work zone. 2. Deformations of, or intrusions into, the occupant compartment should not exceed limits set forth in Section 5.2.2 and Appendix E of MASH 2016.	S U	
	F. The vehicle should remain upright during and after collision. The maximum roll and pitch angles are not to exceed 75 degrees.	S	
	H. Occupant Impact Velocity (OIV) (see Appendix A, Section A5.2.2 of MASH 2016 for calculation procedure) should satisfy the following limits:	S	
	Occupant Impact Velocity Limits		
	Component		Preferred
Longitudinal and Lateral	30 ft/s (9.1 m/s)	40 ft/s (12.2 m/s)	
I. The Occupant Ridedown Acceleration (ORA) (see Appendix A, Section A5.2.2 of MASH 2016 for calculation procedure) should satisfy the following limits:	S		
Occupant Ridedown Acceleration Limits			
Component		Preferred	Maximum
Longitudinal and Lateral	15.0 g's	20.49 g's	
MASH 2016 Test Designation No.		3-10	
Final Evaluation (Pass or Fail)		Fail	

S – Satisfactory U – Unsatisfactory NA - Not Applicable

7 REFERENCES

1. Bielenberg, R.W., Rosenbaugh, S.K., Faller, R.K., Humphrey, B.M., Schmidt, T.L., Lechtenberg, K.A., and Reid, J.D., *MASH Test Nos. 3-17 and 3-11 on a Non-Proprietary Cable Median Barrier*, Report No. TRP-03-303-15, Midwest Roadside Safety Facility, University of Nebraska-Lincoln, Lincoln, Nebraska, November 3, 2015.
2. *Manual for Assessing Safety Hardware (MASH)*, American Association of State Highway and Transportation Officials (AASHTO), Washington, D.C., 2009.
3. *Manual for Assessing Safety Hardware, Second Edition (MASH)*, American Association of State Highway and Transportation Officials (AASHTO), Washington, D.C., 2016.
4. Kohtz, J.E., Bielenberg, R.W., Rosenbaugh, S.K., Faller, R.K., Lechtenberg, K.A., and Reid, J.D., *MASH Test Nos. 3-11 and 3-10 on a Non-Proprietary Cable Median Barrier*, Report No. TRP-03-327-16, Midwest Roadside Safety Facility, University of Nebraska-Lincoln, Lincoln, Nebraska, May 17, 2016.
5. Rosenbaugh, S.K., Hartwell, J.H., Bielenberg, R.W., Faller, R.K., Holloway, J.C., and Lechtenberg, K.A., *Evaluation of Floor pan Tearing and Cable Splices for Cable Barrier Systems*, Report No. TRP-03-324-17, Midwest Roadside Safety Facility, University of Nebraska-Lincoln, Lincoln, Nebraska, May 16, 2017.
6. Meyer, D.T., Lechtenberg, K.A., Faller, R.K., Bielenberg, R.W., Rosenbaugh, S.K., and Reid, J.D., *MASH Test No. 3-10 of a Non-Proprietary, High-Tension, Cable Median Barrier for Use in 6H:1V V-Ditch (Test No. MWP-8)*, Report No. TRP-03-331-17, Midwest Roadside Safety Facility, University of Nebraska-Lincoln, Lincoln, Nebraska, May 10, 2017.
7. Meyer, D.T., Asadollahi Pajouh, M., Lechtenberg, K.A., Faller, R.K., Bielenberg, R.W., and Holloway, J.C., *Phase II Evaluation of Floor pan Tearing for Cable Barrier Systems*, Draft Report No. TRP-03-359-18, Midwest Roadside Safety Facility, University of Nebraska-Lincoln, Lincoln, Nebraska.
8. Hinch, J., Yang, T.L., and Owings, R., *Guidance Systems for Vehicle Testing*, ENSCO, Inc., Springfield, Virginia, 1986.
9. MacInnis, D., Cliff, W., and Ising, K., *A Comparison of the Moment of Inertia Estimation Techniques for Vehicle Dynamics Simulation*, SAE Technical Paper Series – 970951, Society of Automotive Engineers, Inc., Warrendale, Pennsylvania, 1997.
10. Society of Automotive Engineers (SAE), *Instrumentation for Impact Test – Part 1 – Electronic Instrumentation*, SAE J211/1 MAR95, New York City, NY, July, 2007.
11. *Vehicle Damage Scale for Traffic Investigators*, Second Edition, Technical Bulletin No. 1, Traffic Accident Data (TAD) Project, National Safety Council, Chicago, Illinois, 1971.

12. *Collision Deformation Classification – Recommended Practice J224 March 1980*, Handbook Volume 4, Society of Automotive Engineers (SAE), Warrendale, Pennsylvania, 1985.

8 APPENDICES

Appendix A. Material Specifications

Table A-1. Bill of Materials, Test No. MWP-9

Item No.	Description	Material Specification	References
a1	Cable Anchor Base Plate	ASTM A36	N/A
a2	Exterior Cable Plate Gusset	ASTM A36	N/A
a3	Interior Cable Plate Gusset	ASTM A36	N/A
a4	Anchor Bracket Plate	ASTM A36	N/A
a5	3/16" [5] Dia. Brass Rod	ASTM B16-00	H#14-04-05543-2
a6	Release Gusset	A36 Steel	N/A
a7	Release Lever Plate	A36 Steel	N/A
a8	1.25x1.25x0.1875" [32x32x5] TS CT Kicker Lever Tube	ASTM A500 Gr. B	N/A
a9	CMB High Tension Anchor Plate Washer	ASTM A36	H#64047117
a10	1.25x1.25x0.1875" [32x32x5] TS CT Kicker Lever Connecting Tube	ASTM A 500 Gr. B	N/A
a11	3x10x0.5" [76x254x13] Kicker Plate	ASTM A36	N/A
a12	CT kicker - gusset	ASTM A36	N/A
a13	3/4" [19] Dia. Flat Washer	ASTM F844	PFC COC R#14-0082
a14	3/4" [19] Dia. UNC J-Hook Anchor and Hex Nut	J-Hook ASTM A449/Nut ASTM A563 DH	BOLT:H#11618020 NUT: H#1F543
a15	1/4" [6] Dia. Aircraft Retaining Cable, 36" [914] long	7x19 Galv.	N/A
a16	5/8" [16] Dia. Heavy Hex Nut	ASTM A563C	R#14-0343 COC
a17	5/8" [16] Dia. UNC, 9 1/2" [241] Long Hex Bolt	ASTM A449 or SAE J429 Gr. 5	L#490-454-94
a18	24" [610] Dia. Concrete Anchor, 120" [3048] long	4,000 psi fc	T#4156617
a19	#11 Straight Rebar, 114" [2896] long	Grade 60	H#58196113
a20	#4 Anchor Hoop Rebar with 21" [533] Dia.	Grade 60	H#111485
b1	S3x5.7 [S76x8.5] Post by 28 1/8" [714]	ASTM A572 GR50-07, ASTM A709 GR50-09A, ASTM A992-06A	H#59058160
b2	S3x5.7 [S76x8.5] Post by 19" [483]	ASTM A572 GR50-07, ASTM A709 GR50-09A, ASTM A992-06A	H#59058160
b3	#3 Straight Rebar, 43" [1092] long	Grade 60	H#JW12105480
b4	7 1/4" [184] Dia. No. 3 Hoop Reinforcement	Grade 60	H#537484
b5	2 nd Post Keeper Plate, 28 Gauge	ASTM A36	N/A
b7	1/2" [13] Dia. Washer with 1 1/16" [27] OD	ASTM F844	H#A32336, L# 504612
b8	1/2" [13] Dia. and 3/4" [19] Dia. UNC, 2" [51] long Hex Bolt and Nut	Bolt ASTM A307 Gr. A/Nut ASTM A563A	Structural Bolt Distributor's Affidavit O#4CMB
b9	4x3x1/4" [102x76x6] Foundation Tube, 48" [1219] long	ASTM A500 Grade B	H#B200931
b10	2 nd Post Cable Hanger 1/2" [13]	ASTM A36	H#A413247

b11	2 nd Post Anchor Aggregate 12 in. Depth	-	N/A
b12	12" [305] Dia. 2 nd Post Concrete Anchor, 46" [1168] long	4,000 psi f'c	T#4156617
b13	2 nd Post Base Plate 3/8" [10] Thick	ASTM A36	H# A410722
b14	3/16" [5] Dia., 5 1/8" [130] Long Unbent Brass Rod	ASTM B16-00	H#05543-2
c1	3"x1-3/4"x7 Gauge [76x44x4.6], 81 1/4" [2064] Long Midwest Weak Post w/Holes	Hot-Rolled ASTM A1011 HSLA Gr. 50	H#667827 Coil#1131814950 (Post Nos. 3 through 25 and 62 through 74) AND H#438314 Coil#06025311 (Post Nos. 26 through 61)
c2	12 Gauge Tabbed Bracket - Version 10	Hot-Rolled ASTM A1011 HSLA Grade 50	H#6464T3
c3	5/16" [8] Dia. UNC, 1" [25] Long Hex Cap Screw	Bolt SAE J429 Gr. 5 or ASTM A449	H#4208029BA
c3	5/16" [8] Nut	Nut ASTM A563 DH	H#2QG45
c4	Straight Rod - 3/16" [5] Cable Clip	ASTM B16 Brass C36000 Half Hard (HO2), ROUND TS >= 68.0 ksi, YS >= 52.0 ksi	H#198277.1.1
c5	2 1/8"x1 3/8"x7 Gauge [54x35x4.6], 6" [152] Long Bent Steel Plate	Hot-Rolled ASTM A1011 HSLA Gr. 50	H#106387
c6	2 1/8"x1 3/8"x7 Gauge [54x35x4.6], 6" [152] Long Bent Steel Plate	Hot-Rolled ASTM A1011 HSLA Gr. 50	H#106387
c7	3/16" [5] Dia. Brass Cable Clip, 4 9/16" [116] Long Unbent	ASTM B16 Brass C36000 Half Hard (HO2), ROUND, TS >= 68.0 ksi, YS >= 52.0 ksi	H#05543-2
d1	3/4" [19] Dia. 3x7 Cable Guiderail	AASHTO M30-92(2000)/ASTM A741-98 Type 1 Class A coating except with Type 1 minimum breaking strength = 39 kips [173.5 kN]	H#139920/27, H#139015/21
d2	7/8" [22] Dia. Hex Nut	ASTM A563C	H#M643354
d3	Cable End Threaded Rod	ASTM A449	H#133079
d4	Bennet Cable End Fitter	ASTM A47	H#9Q4, H#OP5
	Cable Wedges	ASTM A47	H#DA8
d5	7/8" [22] Dia. Hex Nut	SAE J429 Gr. 5	N/A
e1	Bennet Short Threaded Turnbuckle	Not Specified	KEN Forging Inc. COC
e2	Threaded Load Cell Coupler	N/A	N/A
e3	50,000-lb [222.4-kN] Load Cell	N/A	N/A

Heat Number

Shipper No

Customer PO#

05543-2

323392

Paid by visa

November 2014 supply

MWP Brass SMT

CERTIFICATE OF TEST

Customer: COPPER AND BRASS SALES INC. No 2014-05-26-083
 Invoice No 230605K14 Date 05/26/14
 P.O. No 5400221060 Commodity FREE CUTTING BRASS C36000 HALF HARD IN 12 FT L
 Mill & Country Melting DAECHANG, KOREA Spec PER ASTM B 16/B16M, RV. 2010, B249, ROHS COMPLIANT

Job No.	14-04-	DESCRIPTION			Quantity		Temper	Remarks	B/D No.	Mat No.	Inspection Result	
Line No.	Lot No.	SIZE			Pieces	Wt., Lbs					Dimension	Surface
0010	14686-1 ✓	7/16" (+/-0.0015) DIA, ROUND				5,033	H02			CURD00133	GOOD	GOOD
0020	08516-1	1/4" (+/-0.0015) DIA, ROUND, W/PACKING			944		H02		10	CURD00527	GOOD	GOOD
0020	14689-1 ✓	1/4" (+/-0.0015) DIA, ROUND, W/PACKING			3,790		H02		6 - 9	CURD00527	GOOD	GOOD
0030	14690-1 ✓	3/8" (+/-0.0015) DIA, ROUND				4,923	H02			CURD00231	GOOD	GOOD
0040	14691-1 ✓	7/16" (+/-0.003) DPS, HEXAGON, S.C.			4,687		H02			CUHEX00097	GOOD	GOOD
0050	14692-1 ✓	5/16" (+/-0.0015) DIA, ROUND, W/PACKING			5,015		H02			CURD00289	GOOD	GOOD
0060	05543-2 ✓	3/16" (+/-0.0015) DIA, ROUND, W/PACKING			4,774		H02			CURD00477	GOOD	GOOD
0070	14695-1 ✓	3/8" (+/-0.003) DPS, HEXAGON, S.C.			3,703		H02			CUHEX00246	GOOD	GOOD
0080	14696-1 ✓	1/4" (+/-0.0035) DPS, SQUARE, W/PACKING			1,814		H02			CUSQ00886	GOOD	GOOD
0090	14697-1 ✓	9/32" (+/-0.0015) DIA, ROUND, W/PACKING			2,006		H02			CURD00480	GOOD	GOOD
0100	14687-1 ✓	3/8" (+/-0.0035) DPS, SQUARE				1,825	H02			CUSQ00048	GOOD	GOOD
Chemical/Physical Composition, %	Element	Cu	Pb	Fe			Zn	S/C	T.S., Ksi	Y.S., Ksi	E/L (%)	HRB
	Spec	60.0-63.0	2.50-3.00	0.35 max	-	-	Rem.	Ammonia	-	-	-	-
0010	14686-1	60.8492	2.7492	0.1675	-	-	Rem.	GOOD	64	58	19.8	72.1
0020	08516-1	60.5254	2.7669	0.1766	-	-	Rem.	GOOD	68	56	12.4	78.8
0020	14689-1	60.2003	2.8459	0.1571	-	-	Rem.	GOOD	76	57	10.4	80.6
0030	14690-1	60.2872	2.6908	0.1604	-	-	Rem.	GOOD	67	50	10.7	73.2
0040	14691-1	60.5934	2.6127	0.1305	-	-	Rem.	GOOD	67	54	15.8	79.5
0050	14692-1	60.6773	2.6018	0.1416	-	-	Rem.	GOOD	69	59	10.9	82.2
0060	05543-2	60.5388	2.7248	0.1118	-	-	Rem.	GOOD	75	63	8.5	89.5
0070	14695-1	60.4889	2.7365	0.1339	-	-	Rem.	GOOD	65	54	17.6	79.4
0080	14696-1	60.5934	2.6127	0.1305	-	-	Rem.	GOOD	59	55	15.2	69.3
0090	14697-1	60.6180	2.7040	0.1474	-	-	Rem.	GOOD	72	59	10.7	81.0
0100	14687-1	60.4889	2.7365	0.1339	-	-	Rem.	GOOD	59	46	21.0	64.8

SIGNED FOR DAE CHANG IND.

hysenKrupp Materials NA
 DEL.: 2403436857
 CatOr 31895
 Date 10/08/2014
 NLINE METALS - TX
 345
 5 LR

Figure A-1. 3/16-in. (5-mm) Brass Rod, Test No. MWP-9



US-ML-WILTON
1500-2500 WEST 3RD STREET
WILTON, IA 52778
USA

CUSTOMER SHIP TO STATE STEEL SUPPLY CO INC 13433 CENTECH RD OMAHA, NE 68138-3492 USA		CUSTOMER BILL TO STATE STEEL SUPPLY CO INC SIOUX CITY, IA 51102-3224 USA		GRADE A36	SHAPE / SIZE Flat 1/2 X 3
SALES ORDER 639595/000050		CUSTOMER MATERIAL N°		LENGTH 20'00"	WEIGHT 34,272 LB
CUSTOMER PURCHASE ORDER NUMBER P31101SW251		BILL OF LADING 1334-0000007548		DATE 11/05/2013	
SPECIFICATION / DATE or REVISION 1-ASTM A6/A6M-11 2-A36/A36M-08 3-A709-11 4-AASHTO M270-11					

CHEMICAL COMPOSITION												
C %	Mn %	P %	S %	Si %	Cl %	Ni %	Cr %	Mo %	V %	Nb %	Al %	Pb %
0.18	0.56	0.007	0.036	0.18	0.27	0.08	0.11	0.023	0.000	0.001	0.000	0.0003

CHEMICAL COMPOSITION	
Sn %	0.010

MECHANICAL PROPERTIES						
Elong. %	G/L Inch	UTS PSI	UTS MPa	YS PSI	YS MPa	
26.30	8.000	66800	461	43700	301	
30.00	8.000	67600	466	44100	304	

GEOMETRIC CHARACTERISTICS	
R-R	20.52

COMMENTS / NOTES

4CMB Cable Anchor Plate Washer



The above figures are certified chemical and physical test records as contained in the permanent records of company. This material, including the billets, was melted and manufactured in the USA. CMTR complies with EN 10204 3.1.

Bhaskar
BHASKAR YALAMANCHILI
QUALITY DIRECTOR

Brett Krause
BRETT KRAUSE
QUALITY ASSURANCE MGR.

Figure A-2. CMB High Tension Anchor Plate Washer, Test No. MWP-9

Low Deflection Washers R#14-0082
3/4" AND 1" Washers



Porteous Fastener Company
BOLTS NUTS SCREWS WASHERS

CORPORATE OFFICE
1040 Watson Center Road, Carson, CA 90745
(310) 549-9180 Fax (310) 835-0415
www.porteousfastener.com

February 7, 2013

Attn: Chris

The Structural Bolt

Dear: Chris,

You contacted our Denver office and requested that I write to you concerning specifications under which we purchase our **USS Flat Washers**

Firstly, our products are purchased to specifications where applicable. Our Purchase Orders clearly state that each product supplied to Porteous Fastener Company is to meet the proper specification as referenced in the Industrial Fastener Institute manual for that product when such specifications exist.

(ANSI B18.22.1 and ASTM F844. All HDG plating shall be done per ASTM A153)

Secondly, we require certifications from our suppliers of all products Grade 5 or better: A325 Structural Bolts, Grade 5 Hex Cap Screws, Grade 8 Hex Cap Screws, ASTM A194 2H Hvy, Hex Nuts, F436 Structural Washers, Grade 8 Finished Hex Nuts, ASTM A193 Grade B7 Threaded Rod, SAE Hi Nuts and Grade C Hex Locknuts. These certifications are on file at Porteous corporate office and copies of same are available to our customers.

We trust that you can be confident, as we are, that the product furnished to you meets specifications.

Please let me know if we can be of further service.

Sincerely,
Herbert Recinos
Inventory Control
Cc: Mike Hall – Denver

Figure A-3. 3/4-in (19-mm) Dia. Flat Washer, Test No. MWP-9

AUG/23/2012/THU 02:08 PM TSA MANUFACTURING

FAX No. 4028953297

P. 001/001

P.O. # 145117

PO# 30078 SO# 89068

Item: 3/4-10 X 18 1/4 J HOOK ANCHOR			
Material Specification: ASTM A449			
LOT#:	11618020		
Heat Number:	11618020		
Tensile Strength PSI:	131800 PSI	Yield Strength PSI:	121800 PSI
Elongation:	20	Reduction of Area:	58
Hardness:	27 HRC	Proof Load:	NA
Macro Etch:	NA	Tempering Temp.:	1340 F

Carbon (C):	0.44	Chromium (CR):	NA
Manganese (MN):	0.71	Molybdenum (MO):	NA
Phosphorus (P):	0.013	Copper (CU):	NA
Sulfur (S):	0.034	Nitrogen (N):	NA
Silicon (SI):	0.19	Nickel (NI):	NA
Cobalt (CO):	NA	Aluminum (AL):	NA
Vanadium (V):	NA	Tin (SN):	NA
Tungsten (W):	NA	Titanium (TI):	NA
Columbium/Niobium (NB/CB):	NA	Boron (B):	NA
Calcium (CA):	NA		

We hereby certify that the material was manufactured, sampled, tested and inspected per the most recent revision of the or material specification. The foregoing data was furnished to us by our supplier or resulting from a test performed in a recognized laboratory and is on file in the records of the corporation.
Name: Kayla Patterson Date: 08.13.12

Figure A-4. J-Hook Anchor Bolts, Test No. MWP-9

NOV-08-2005 TUE 05:33 PM

FAX NO.

P. 05

TEST CERTIFICATE	
Purchaser: 潤昌機械工業股份有限公司	
Order NO: PO# P178277	Inspection date: 9/18/2005
S/C NO: PI# 050524-T37	Issue date: 09/20/2005
LOT NO: 8VQ	
Size: 3/4-10 ASTM A563 Grade DH Heavy Hex Nuts - Hot Dip Galvanized O/S: 0.50MM Marked "DH" + Makers Sign + "DIGO"	
Quantity: 54,000PCS	180CTNS
Vessel Name: APL THAILANO / 089E	

Material: C-CH40ACR

Heat NO.	Size Diameter	C	Mn	P	S	Si
IF543	28.00mm	100%	100%	1000%	1000%	100%
		43	81	20	10	5

Dimensional Inspections Specification: ANSI B18.2.2-1987

UNIT: inch

Characteristic	Specification	Actual Result	Ac.	Re.
Visual appearance	ASTM F812-2002	OK	32	0
Width across flats	1.250-1.212	1.233-1.224	32	0
Width across corners	1.443-1.382	1.405-1.395	32	0
Nuts thickness	0.758-0.710	0.736-0.721	32	0
Hole diameter	0.683-0.662	0.679-0.670	32	0
Thread	ASME B1.1-2002	OK	32	0

Mechanical Properties Specification: ASTM A563-04a

Characteristic	Requirement	Result	Ac.	Re.
Hardness	HRC 24-38	HRC30.9-33.0	8	0
Proof Load	Min 50100Lbf	58960Lbf	8	0


Signatory: 
Y.M. WANG/Q.C. MANAGER

Figure A-5. 3/4-in. (19-mm) Dia. Heavy Hex Nut, Test No. MWP-9



Porteous Fastener Company
BOLTS NUTS SCREWS WASHERS

CORPORATE OFFICE
1040 Watson Center Road, Carson, CA 90745
(310) 549-9180 Fax (310) 835-0415
www.porteousfastener.com

May 30, 2013

Attn: Chris Burris

Structural Bolt
2140 Cornhusker Hwy
Lincoln NE 68521
Fax: 402-435-3135

Dear: Chris,

You contacted our Denver office concerning specifications under which we purchase our **N.C. Gr. 5 Hex Cap Screws**.

Firstly, our products are purchased to specification where applicable. Our Purchase Orders clearly state that each product supplied to Porteous Fastener Company is to meet the proper specification as referenced in the Industrial Fastener Institute manual for that product when such specifications exist.

(ASME / ANSI B18.2.1 and SAE J429, GRADE 5.)

Secondly, we require certifications from our suppliers of all products Grade 5 or better: A325 Structural Bolts, Grade 5 Hex Cap Screws, Grade 8 Hex Cap Screws, ASTM A194 2H Hvy, Hex Nuts, F436 Structural Washers, Grade 8 Finished Hex Nuts, ASTM A193 Grade B7 Threaded Rod, SAE Hi Nuts and Grade C Hex Locknuts. These certifications are on file at Porteous corporate office and copies of same are available to our customers.

We trust that you can be confident, as we are, that the product furnished to you meets specifications.

Please let me know if we can be of further service.

Sincerely,

Herbert Recinos
Inventory Control

Cc: Carrie- Denver

Figure A-6. $\frac{5}{8}$ -in. (16-mm) Dia. Heavy Hex Nut, Test No. MWP-9

Shipment Date: 04/18/2012

KANEBRIDGE CORPORATION
CERTIFICATE OF CONFORMANCE

Company:
HODELL-NATCO IND.
11688 FAIRGROVE IND. BLVD.
MARYLAND HEIGHTS, MO 63043
Attn: ONL/DANIEL

P.O. #: 4137087
Sales Order #: 4678123
Shipment #: 3243260

<u>Item Number</u>	<u>Description</u>	<u>Lot No</u>	<u>Cert Ref</u>
62152CH50	5/8-11X9 1/2 COAR HEX CAP SCR GR5 ZINC	490-454-94	1
	<u>Origin:</u> CANADA	<u>Mfr:</u> 1110615263157G	

CertRef Certification Description

1 WE CERTIFY THAT THIS ITEM WAS MANUFACTURED TO SAE J429 SPECIFICATIONS. THE MANUFACTURER'S CHEMICAL AND PHYSICAL TEST REPORTS CERTIFYING THIS PART TO SAE J429 ARE ON FILE AND AVAILABLE AT ANY TIME UPON REQUEST. ADDITIONALLY, THEY HAVE NOT COME INTO CONTACT WITH MERCURY WHILE IN OUR POSSESSION.

Signed: RICK SAUL
Title: Certification Department

Claims against Kanebridge Corporation shall be limited to a refund or credit for the price billed or paid for improper merchandise. Seller shall not be responsible for buyer's manufacturing costs, labor, alternate purchases, extra freight, replating, plating, lost profit, good will, recall costs, or other incidental or consequential damages.

Figure A-7. 5/8-in. (16-mm) Dia. UNC, 9 1/2-in. (241-mm) Long Hex Bolt, Test No. MWP-9

CAUTION
FRESH CONCRETE

Body and or eye contact with fresh (moist) concrete should be avoided because it contains alkali and is caustic.

Ready Mixed Concrete Company
6200 Cornhusker Highway, P.O. Box 29288
Lincoln, Nebraska 68529
Telephone 402-434-1844

PLANT	MIX CODE	YARDS	TRUCK	DRIVER	DESTINATION	CLASS	TIME	DATE	TICKET
04	25513000	3.00	0135	056			10:23 AM	03/12/14	4156617
CUSTOMER	JOB	CUSTOMER NAME			TAX CODE	PARTIAL	NIGHT R.	LOADS	
00003		CIA--MIDWEST ROADSIDE SAFETY						1	
DELIVERY ADDRESS			SPECIAL INSTRUCTIONS				P.O. NUMBER		
4800 NW. 35TH			N OF N GOODYEAR HANGER				402-450-6250		

LOAD QUANTITY	CUMULATIVE QUANTITY	ORDERED QUANTITY	PRODUCT CODE	PRODUCT DESCRIPTION	UNIT PRICE	AMOUNT
3.00	3.00	3.00	25513000	L5500 (HE) .40 MINIMUM HAUL WINTER SERVICE	104.91	314.73
						40.00
						12.00
						366.73

WATER ADDED ON JOB
AT CUSTOMER'S REQUEST

Ø

GAL.

RECEIVED BY *MWRKJ*


SUBTOTAL
TAX
TOTAL

366.73
366.73


TRUCK	USER LOGIN	DISP	TICKET NUM	TICKET NUM	TICKET ID	TIME	DATE			
0135	056R		4156617	176448	191052	10:23	03/12/2014			
LOAD SIZE	MIX CODE					SEQ	LOAD ID			
3.00 yd	25513000					W	193341			
MATERIAL	SOURCE	DESIGN	QTY	REQUIRED	BATCHED	VAR	% VAR	%MOISTURE	ACTUAL WAT	
647B	47B GRAVEL	1915.0	1b	5825.4	1b	5800.0	-25.4	-0.44%	1.40 M	9.60 gl
L47B	47B ROCK	833.0	1b	2509.0	1b	2500.0	-9.0	-0.36%	0.40 M	1.19 gl
CEM1	CEMENT TYP	752.0	1b	2256.0	1b	2245.0	-11.0	-0.49%		
LWR	POZZ 322N	23.0	oz	69.0	oz	69.0	0.0	0.00%		
AIR	MB-AE 90 A	3.0	oz	9.0	oz	9.0	0.0	0.00%		
WATER	WATER	34.0	gl	94.2	gl	94.9	0.7	0.74%		94.91 gl
WATER2	RECYCLE WA	0.0	gl	0.0	gl	0.0	0.0	0.00%		
NON-SIMULATED NUM BATCHES: 1										
LOAD TOTAL: 11342 lb DESIGN W/C: 0.377 WATER/CEMENT: 0.393A DESIGN WATER: 102.0 gl ACTUAL WATER: 105.7 gl										
SLUMP: 4.00 " # WATER IN TRUCK: 0.0 gl										

MWP-1 Concrete Anchorage (6:1 Slope)
R# 14-0353 SMT

Figure A-8. Concrete Anchor, Test No. MWP-9

CERTIFIED MATERIAL TEST REPORT												Page 1/1		
 US-ML-MIDLOTHIAN 300 WARD ROAD MIDLOTHIAN, TX 76065 USA		CUSTOMER SHIP TO NEBCO INC STEEL DIVISION HAVELOCK, NE 68529 USA				CUSTOMER BILL TO CONCRETE INDUSTRIES INC LINCOLN, NE 68529-0529 USA				GRADE 60/420		SHAPE / SIZE REBAR ROUND / #11 (36MM)		
		SALES ORDER 126287/000020				SPECIFICATION / DATE or REVISION ASTM A615/A615M-09B								
		CUSTOMER PURCHASE ORDER NUMBER 95510			BILL OF LADING 1327-0000015536			DATE 08/01/2012			LENGTH 60'00"		WEIGHT 33,790 LB	HEAT / BATCH 5819611302
CHEMICAL COMPOSITION														
C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Sn	V	Nb	Al		
%	%	%	%	%	%	%	%	%	%	%	%	%		
0.44	0.87	0.012	0.022	0.23	0.24	0.07	0.09	0.027	0.007	0.025	0.021	0.002		
CHEMICAL COMPOSITION CEA706 % 0.60														
MECHANICAL PROPERTIES														
YS		YS		UTS		G/L		G/L		Elong.				
KSI		MPa		MPa		Inch		mm		%				
73.4		506		730		8.000		200.0		12.90				
MECHANICAL PROPERTIES Bend tes OK														
COMMENTS / NOTES														

The above figures are certified chemical and physical test records as contained in the permanent records of company. This material, including the billets, was melted and manufactured in the USA. We certify that these data are correct and in compliance with specified requirements. CMTR complies with EN 10204 3.1.


 BHASKAR YALAMANCHILI
 QUALITY DIRECTOR



 TOM HARRINGTON
 QUALITY ASSURANCE MGR.

Figure A-9. #11 Rebar for Anchorage, Test No. MWP-9



P.O. Box 316
 Pueblo, CO 81002 USA

MATERIAL TEST REPORT
 Date Printed: 21-MAR-12

Date Shipped: 21-MAR-12	Product: DEF 13mm	Specification: ASTM-A-615M09b GR 420/ASTM-A-706M09b
FWIP: 52815348	Customer: CONCRETE INDUSTRIES INC	Cust. PO: 93051

Heat Number	CHEMICAL ANALYSIS															
	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	V	B	Ca	Sn	N	Ti
111485	0.27	1.23	0.012	0.024	0.24	0.31	0.13	0.10	0.044		0.046	0.0003		0.014	0.0108	0.001
Carbon Equivalent = 0.494																

Heat Number	Sample No.	MECHANICAL PROPERTIES					Bend	Wt/ft
		Yield (Psi)	Ultimate (Psi)	Elongation (%)	Reduction (%)			
111485	01	74160	103330	14.4		ok	0.664	
		(MPa) 511.3	712.4					
111485	02	74037	102730	15.6		ok	0.663	
		(MPa) 510.5	708.3					

All melting and manufacturing processes of the material subject to this test certificate occurred in the United States of America.
 ERMS also certifies this material to be free from Mercury contamination.
 This material has been produced and tested in accordance with the requirements of the applicable specifications. We hereby certify that the above test results represent those contained in the records of the Company.

Mark S. [Signature]
 Quality Assurance Department

Figure A-10. #4 Rebar for Anchorage, Test No. MWP-9



US-ML-MIDLOTHIAN
300 WARD ROAD
MIDLOTHIAN, TX 76065
USA

CERTIFIED MATERIAL TEST REPORT

CUSTOMER SHIP TO STEEL & PIPE SUPPLY CO INC 1003 FORT GIBSON RD CATOOSA,OK 74015-3033 USA		CUSTOMER BILL TO STEEL & PIPE SUPPLY CO INC MANHATTAN,KS 66505-1688 USA		GRADE A36/A57250	SHAPE / SIZE Standard I-Beam / 3 X 5.7# / 75 X 8.5		
SALES ORDER 812105/000020		CUSTOMER MATERIAL N° 0000000003537040		LENGTH 40'00"	WEIGHT 8,208 LB	HEAT / BATCH 59058160/03	
CUSTOMER PURCHASE ORDER NUMBER 4500221191			BILL OF LADING 1327-0000099969	DATE 04/02/2014	SPECIFICATION / DATE or REVISION A36/A36M-08 A572/A572M-07 ASTM A6/A6M-11		

CHEMICAL COMPOSITION												
C %	Mn %	P %	S %	Si %	Cu %	Ni %	Cr %	Mo %	Sn %	V %	Nb %	Al %
0.09	0.79	0.014	0.026	0.20	0.36	0.11	0.06	0.027	0.009	0.001	0.011	0.003

CHEMICAL COMPOSITION	
CEqvA6 %	0.3

MECHANICAL PROPERTIES					
YS KSI	UTS KSI	YS MPa	UTS MPa	G/L inch	G/L mm
53.4	69.5	382	468	8.000	200.0
55.3	67.9	368	479	8.000	200.0

MECHANICAL PROPERTIES	
Elong. %	Y/T rati %
23.20	0.786
23.60	0.796

COMMENTS / NOTES

4 Cable MWP 6-2part Posts
R#15-0500
April 2015 SMT

The above figures are certified chemical and physical test records as contained in the permanent records of company. This material, including the billets, was melted and manufactured in the USA. CMTR complies with EN 10204 3.1.

Maskay BHASKAR YALAMANCHILI
QUALITY DIRECTOR

Tom Harrington TOM HARRINGTON
QUALITY ASSURANCE MGR.

123

Figure A-11. S3x5.7 (S76x8.5) Posts – 28¹/₈ in. (714 mm) and 19 in. (483 mm) Long, Test No. MWP-9

SOLD ADELPHIA METALS I LLC
TO: 411 MAIN ST E
NEW PRAGUE, MN 56071-



CERTIFIED MILL TEST REPORT

Page: 1

SHIP ADELPHIA METALS-CUST PU
TO: N/A
JEWETT, TX 75846-

Ship from:
Nucor Steel - Texas
8812 Hwy 79 W
JEWETT, TX 75846
800-527-6445

Date: 25-Jul-2012
B.L. Number: 611543
Load Number: 217850

Material Safety Data Sheets are available at www.nucorbar.com or by contacting your inside sales representative.

NBMG-08 January 1, 2012

LOT # HEAT #	DESCRIPTION	PHYSICAL TESTS					CHEMICAL TESTS												
		YIELD P.S.I.	TENSILE P.S.I.	ELONG % IN 8"	BEND	WT% DEF	C	Ni	Mn	Cr	P	Mo	S	V	Si	Cb	Cu	Sn	C.E.
PO# => 804132																			
JW1210548001	Nucor Steel - Texas	77,800	111,200	12.0%			.38	.86	.012	.026	.14	.38	.56						
JW12105480	10/#3 Rebar 40' A615M GR 420 (Gr60) ASTM A615/A615M-12 GR 60[420] AASHTO M31-07	536MPa	767MPa				.17	.18	.045	.015	.002								

I hereby certify that the material described herein has been manufactured in accordance with the specifications and standards listed above and that it satisfies those requirements.
1.) Weld repair was not performed on this material.
2.) Melted and Manufactured in the United States.
3.) Mercury, Radium, or Alpha source materials in any form have not been used in the production of this material.

QUALITY ASSURANCE: Nathan Stewart

Figure A-12. #3 Rebar for Anchorage, Test No. MWP-9

EVRAZ ROCKY MOUNTAIN STEEL
A DIVISION OF EVRAZ INC. NA
P.O. Box 316
Pueblo, CO 81002 USA

MATERIAL TEST REPORT
Date Printed: 16-DEC-10

Date Shipped: 16-DEC-10	Product: DEF 10mm	Specification: ASTM-A-615M09b GR 420/ ASTM-A-706M09I
FWIP: 52815347	Customer: CONCRETE INDUSTRIES INC	Cust. PO: 86205

Heat Number	CHEMICAL ANALYSIS														(Heat cast 09/27/10)	
	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	V	B	Cb	Sn	N	Ti
537484	0.26	1.24	0.015	0.007	0.24	0.25	0.08	0.14	0.013	0.004	0.037	0.0006	0.000	0.013	0.0081	0.002
Carbon Equivalent = 0.487																

Heat Number	Sample No.	MECHANICAL PROPERTIES							Wt/ft ³
		Yield (Psi)	Ultimate (Psi)	Elongation (%)	Reduction (%)	Impact Bend			
537484	01	68260	98900	17.3		OK	0.372		
		(MPa) 470.6	681.9						
537484	02	66012	96040	16.5		OK	0.372		
		(MPa) 455.1	662.2						

All melting and manufacturing processes of the material subject to this test certificate occurred in the United States of America.
ERMS also certifies this material to be free from Mercury contamination.
This material has been produced and tested in accordance with the requirements of the applicable specifications. We hereby certify that the above test results represent those contained in the records of the Company.

Mark S. [Signature]
Quality Assurance Department

Figure A-13. 7¼-in. (184-mm) Dia. #3 Hoop Rebar, Test No. MWP-9

SUPERIOR WASHER AND GASKET CORP.
170 Adams Avenue
Hauppauge, New York 11788
Phone: (631) 273-8282
Fax: (631) 273-8088
E-Mail: swg@superiorwasher.com
Web: superiorwasher.com
(In the East)

SUPERIOR WASHER AND GASKET CORP.
662 Bryant Blvd.
Rock Hill, South Carolina 29732
Phone: (803) 366-3250
Fax: (803) 366-3511
E-Mail: swg@superiorwasher.com
Web: superiorwasher.com
(In the South)

ACCURATE MANUFACTURE GROUP
P.O. BOX 7232 - DEPT. 168

INDIANAPOLIS, IN 46206

Customer Purchase Order Number 9454		Superior Order Number 504612-1	Superior Lot Number 504612 - 1	Tracer No. SC31483 -3 /21153114
Date 04-02-13	Production Card 175383	Part Number WASB12NZ		Quantity 15,000
Drawing P/N S-1/2TYBNZ A		Dual Cert No.		

We hereby certify that all materials and processes conform to the required drawing specifications and that the parts have been manufactured in the U.S.A.
All parts are manufactured in a Mercury-free environment

Material

1008 LOW CARBON STEEL No. 5

ZINC TRIVALENT CHROMIUM

Chemical Analysis

C	CARBON	.0700
Mn	MANGANESE	.3300
P	PHOSPHORUS	.0080
S	SULPHUR	.0070
Si	SILICON	.0100
Cr	CHROMIUM	.0200
Ni	NICKEL	.0100
Mo	MOLYBDENUM	.0100
Cu	COPPER	.0200
Fe	IRON	
Ti	TITANIUM	
Co	COBALT	
N	NITROGEN	
Cb	COLUMBIUM	
Al	ALUMINIUM	.0430
Sn	TIN	
Mg	MAGNESIUM	
Zn	ZINC	
Pb	LEAD	
Va	VANADIUM	

Mechanical Properties

Yield	
Tensile	
Elongation	
Hardness	B 49.0
Heat	4179170
Magnetic	
Permeability	
Bend Test	

SUPERIOR WASHER & GASKET CORP.

By *Richard Anderson, Jr.*
Richard Anderson, Jr.
Quality Control Manager

Figure A-14. 1/2-in. (13-mm) Washers, Test No. MWP-9



DISTRIBUTOR'S AFFIDAVIT

DISTRIBUTOR:
 THE STRUCTURAL BOLT CO
 2140 CORNHUSKER HWY
 LINCOLN, NE 68521

REFERENCE PO# 4CMB

The Strcutrual Bolt Co, hereby certifies that the items below meets or exceeds requirements per your purchase order

Quantity	Size	Description	Spec	Finish
20	3/4 x 5-1/2	HEX BOLT	A307	PL
20	3/4-10 NUT	HEX NUT	A307	PL
100	1/2 WASHER	FLAT WASHER	A307	PL
50	1/2-13 X 2	HEX BOLT	A307	PL
50	1/2-13 NUT	HEX NUT	A307	PL

Order# 4CMB
 TSBC Inv# 108423

Distributor's Signature Chris Barris Date: 2/18/2014
 Title: General Manager

Figure A-15. Hex Bolts and Nuts – 1/2-in. (13-mm) Dia. UNC, 2-in. (51-mm) Long and 3/4-in. (19-mm) Dia. UNC, 5 1/2-in. (140-mm) Long, Test No. MWP-9

26Apr12 9:26 TEST CERTIFICATE No: MAR 877775

INDEPENDENCE TUBE CORPORATION
6226 W. 74TH STREET
CHICAGO, IL 60638
Tel: 708-496-0380 Fax: 708-563-1950

F/O No 4500179833
Rel
S/O No MAR 212696-001
B/L No MAR 123862-004 Shp 23Apr12
Inv No Inv

Sold To: (5017)
STEEL & PIPE SUPPLY
401 NEW CENTURY PARKWAY
KANSAS CITY WHSE.
NEW CENTURY, KS 66031

Ship To: (1)
STEEL & PIPE SUPPLY
401 NEW CENTURY PKWY
NEW CENTURY, KS 66031

Tel: 913-768-4333 Fax: 913 768-6683

CERTIFICATE of ANALYSIS and TESTS

Cert. No: MAR 877775
19Apr12

Part No
TUBING A500 GRADE B(C)
4" X 3" X 1/4" X 40'

Pcs Wgt
20 8,408

Heat Number Tag No
B200931 621072

Pcs Wgt
20 8,408

YLD=69070/TEN=81790/ELG=23.9

Heat Number
B200931

*** Chemical Analysis ***

C=0.2000 Mn=0.4500 F=0.0120 S=0.0020 Si=0.0300 Al=0.0330
Cu=0.1200 Cr=0.0400 Mo=0.0100 V=0.0010 Ni=0.0400

WE PROUDLY MANUFACTURE ALL OF OUR HSS IN THE USA.
INDEPENDENCE TUBE PRODUCT IS MANUFACTURED, TESTED,
AND INSPECTED IN ACCORDANCE WITH ASTM STANDARDS.

CURRENT STANDARDS:

.....A500/A500M-10a
.....A513-07
.....A252-98 (2002)

Figure A-16. Foundation Tube, Test No. MWP-9



SPS Coil Processing Tulsa
5275 Bird Creek Ave.
Port of Catoosa, OK 74015

METALLURGICAL TEST REPORT

PAGE 1 of 1
DATE 02/05/2015
TIME 16:05:32
USER MEHEULAL

S
O
L
D
T
O

S
H
I
P
T
O
13713
Warehouse 0020
1050 Fort Gibson Rd
CATOOSA OK 74015

Order	Material No.	Description	Quantity	Weight	Customer Part	Customer PO	Ship Date
40237114-0040	701672120TM	1/2 72 X 120 A36 TEMPERPASS STPMLPL	8	9,801.600			02/05/2015

Chemical Analysis

Heat No.	Vendor	DOMESTIC										Milled and Manufactured in the USA			
Batch		STEEL DYNAMICS COLUMBUS										Produced from Coil			
Carbon	Manganese	Phosphorus	Sulphur	Silicon	Nickel	Chromium	Molybdenum	Boron	Copper	Aluminum	Titanium	Vanadium	Columbium	Nitrogen	Tin
A413247	STEEL DYNAMICS COLUMBUS	8 EA 9,801.600 LB										Melted and Manufactured in the USA			
0003769220												Produced from Coil			
0.2000	0.8000	0.0110	0.0020	0.0300	0.0400	0.0700	0.0100	0.0001	0.0900	0.0300	0.0010	0.0030	0.0010	0.0068	0.0070

Mechanical/ Physical Properties

Mill Coil No.	Tensile	Yield	Elong	Rckwl	Grain	Charpy	Charpy Dr	Charpy Sz	Temperature	Olsen
A413247-01	74800.000	49800.000	32.10			0	NA			
	73300.000	47900.000	32.70			0	NA			

Chemical Analysis

Heat No.	Vendor	DOMESTIC										Milled and Manufactured in the USA			
Batch		STEEL DYNAMICS COLUMBUS										Produced from Coil			
Carbon	Manganese	Phosphorus	Sulphur	Silicon	Nickel	Chromium	Molybdenum	Boron	Copper	Aluminum	Titanium	Vanadium	Columbium	Nitrogen	Tin
A413247	STEEL DYNAMICS COLUMBUS	7 EA 8,576.400 LB										Melted and Manufactured in the USA			
0003769231												Produced from Coil			
0.2000	0.8000	0.0110	0.0020	0.0300	0.0400	0.0700	0.0100	0.0001	0.0900	0.0300	0.0010	0.0030	0.0010	0.0068	0.0070

Mechanical/ Physical Properties

Mill Coil No.	Tensile	Yield	Elong	Rckwl	Grain	Charpy	Charpy Dr	Charpy Sz	Temperature	Olsen
A413247-01	74800.000	49800.000	32.10			0	NA			
	73300.000	47900.000	32.70			0	NA			

THE CHEMICAL, PHYSICAL, OR MECHANICAL TESTS REPORTED ABOVE ACCURATELY REFLECT INFORMATION AS CONTAINED IN THE RECORDS OF THE COMPANY.

Figure A-17. 2nd Post Cable Hanger, 1/2 in. (13 mm) Thick, Test No. MWP-9

129

MWRSF Report No. TRP-03-360-18
March 30, 2018

CAUTION
FRESH CONCRETE

Body and or eye contact with fresh (moist) concrete should be avoided because it contains alkali and is caustic.

Ready Mixed Concrete Company
6200 Cornhusker Highway, P.O. Box 29288
Lincoln, Nebraska 68529
Telephone 402-434-1844

PLANT	MIX CODE	YARDS	TRUCK	DRIVER	DESTINATION	CLASS	TIME	DATE	TICKET
04	25513000	3.00	0135	056			10:23A	03/12/14	4156617
CUSTOMER	JOB	CUSTOMER NAME			TAX CODE	PARTIAL	NIGHT R.	LOADS	
00003		CIA--MIDWEST ROADSIDE SAFTEY						1	
DELIVERY ADDRESS			SPECIAL INSTRUCTIONS				P.O. NUMBER		
4800 NW. 35TH			N OF N GOODYEAR HANGER				402-450-6250		

LOAD QUANTITY	CUMULATIVE QUANTITY	ORDERED QUANTITY	PRODUCT CODE	PRODUCT DESCRIPTION	UNIT PRICE	AMOUNT
3.00	3.00	3.00	25513000	L5500 (HE) .40 MINIMUM HAUL WINTER SERVICE	104.91	314.73
						40.00
						12.00
						366.73

WATER ADDED ON JOB
AT CUSTOMER'S REQUEST

Ø

GAL.

RECEIVED BY *MWRKJ*

SUBTOTAL
TAX
TOTAL

366.73
366.73

TRUCK	USER LOGIN	DISP	TICKET NUM	TICKET NUM	TICKET ID	TIME	DATE	
0135	OSER		4156617	176448	191052	10:23	03/12/2014	
LOAD SIZE	MIX CODE					SEQ	LOAD ID	
3.00 yd	25513000					W	193341	
MATERIAL	SOURCE	DESIGN QTY	REQUIRED	BATCHED	VAR	% VAR	%MOISTURE	ACTUAL WAT
647B	47B GRAVEL	1915.0 lb	5825.4 lb	5800.0	-25.4	-.44%	1.40 M	9.50 gl
L47B	47B ROCK	833.0 lb	2509.0 lb	2500.0	-9.0	-.36%	0.40 M	1.19 gl
CEM1	CEMENT TYP	752.0 lb	2256.0 lb	2245.0	-11.0	-.49%		
LWR	POZZ 322N	23.0 oz	69.0 oz	69.0	0.0	0.00%		
AIR	MB-AE 90 A	3.0 oz	9.0 oz	9.0	0.0	0.00%		
WATER	WATER	34.0 gl	94.2 gl	94.9	0.7	0.74%		94.91 gl
WATER2	RECYCLE WA	0.0 gl	0.0 gl	0.0	0.0	0.00%		
NON-SIMULATED NUM BATCHES: 1								
LOAD TOTAL: 11342 lb DESIGN W/C: 0.377 WATER/CEMENT: 0.393A DESIGN WATER: 102.0 gl ACTUAL WATER: 105.7 gl								
SLUMP: 4.00 "# WATER IN TRUCK: 0.0 gl								

MWP-1 Concrete Anchorage (6:1 Slope)
R# 14-0353 SMT

Figure A-18. 12-in. (305-mm) Dia. 2nd Post Concrete Anchor, Test No. MWP-9



SPS Coil Processing Tulsa
5275 Bird Creek Ave.
Port of Catoosa, OK 74015

METALLURGICAL TEST REPORT

PAGE 1 of 1
DATE 01/23/2015
TIME 11:13:42
USER WILLIAMR

S
O
L
D
T
O

S
H
I
P
T
O

13713
Warehouse 0020
1050 Fort Gibson Rd
CATOOSA OK 74015

Order	Material No.	Description	Quantity	Weight	Customer Part	Customer PO	Ship Date
40235941-0020	701272120TM	3/8 72 X 120 A36 TEMPERPASS STPMLPL	5	4,596			01/23/2015

Chemical Analysis

Heat No.	Vendor	DOMESTIC										Mill	Melted and Manufactured in the USA				
Batch		5 EA		4,596 LB								Produced from Coil					
Carbon	Manganese	Phosphorus	Sulphur	Silicon	Nickel	Chromium	Molybdenum	Boron	Copper	Aluminum	Titanium	Vanadium	Columbium	Nitrogen	Tin		
A410722	STEEL DYNAMICS COLUMBUS	0.2000	0.8800	0.0160	0.0010	0.0200	0.0500	0.0700	0.0100	0.0001	0.0900	0.0280	0.0020	0.0030	0.0020	0.0073	0.0040

Mechanical/ Physical Properties

Mill Coil No.	Tensile	Yield	Elong	Rckwl	Grain	Charpy	Charpy Dr	Charpy Sz	Temperature	Olsen
A410722-04	73700.000	50200.000	32.00			0	NA			
	70900.000	47900.000	32.80			0	NA			
	72100.000	48800.000	33.30			0	NA			
	70200.000	47100.000	31.20			0	NA			

Chemical Analysis

Heat No.	Vendor	DOMESTIC										Mill	Melted and Manufactured in the USA				
Batch		10 EA		9,192 LB								Produced from Coil					
Carbon	Manganese	Phosphorus	Sulphur	Silicon	Nickel	Chromium	Molybdenum	Boron	Copper	Aluminum	Titanium	Vanadium	Columbium	Nitrogen	Tin		
A410722	STEEL DYNAMICS COLUMBUS	0.2000	0.8800	0.0160	0.0010	0.0200	0.0500	0.0700	0.0100	0.0001	0.0900	0.0280	0.0020	0.0030	0.0020	0.0073	0.0040

Mechanical/ Physical Properties

Mill Coil No.	Tensile	Yield	Elong	Rckwl	Grain	Charpy	Charpy Dr	Charpy Sz	Temperature	Olsen
A410722-04	73700.000	50200.000	32.00			0	NA			
	70900.000	47900.000	32.80			0	NA			
	72100.000	48800.000	33.30			0	NA			
	70200.000	47100.000	31.20			0	NA			

THE CHEMICAL, PHYSICAL, OR MECHANICAL TESTS REPORTED ABOVE ACCURATELY REFLECT INFORMATION AS CONTAINED IN THE RECORDS OF THE COMPANY.

131

Figure A-19. 2nd Post Base Plate, 3/8 in. (10 mm) Thick, Test No. MWP-9

MwRSF Report No. TRP-03-360-18
March 30, 2018

ThyssenKrupp Steel USA

1 ThyssenKrupp Drive
Calvert, Al. 36513



Mill Certificate

CUSTOMER ORIGINAL

Order - Item 42820-70	Certificate Number 1131814950	Delivery No 80554939-10	Ship Date 02/27/2014	Page 1 of 1						
Customer No: 10779		Cust PO: 01013159								
Customer Part No: 26576										
Customer Sold to: Norfolk Iron & Metal Company 3001 North Victory Rd. NORFOLK NE 68702 USA		Customer Ship to: Norfolk Iron & Metal Company 3001 North Victory Rd. NORFOLK NE 68702 USA		Contact - Customer Service Company ThyssenKrupp Steel USA P.O. Box 456 CALVERT AL 36513 USA Email: CS.Calvert@Thyssenkrupp.com Ph : 1-251-289-3000						
Steel Grade / Customer Specification Hot Roll Black Coil HSLAS-F GRADE 50 [340] / 0.1750 " X 60.0000 " ACCORDING TO A1011 {Light < 0.230"(6.0 mm)}										
Type of Product/Surface Hot Roll Black Coil Semi exposed										
TEST METHOD ASTM										
MATERIAL DESCRIPTION										
	ORDERED	Heat No.	Coil No.	Weight Net LB	Weight Gross LB					
(mm)	4.445	667827	1131814950	47,818	47,818					
(in)	0.1750									
CHEMICAL COMPOSITION OF THE LADLE *										
Heat No.	C	Si	Mn	P	S	Al	Cr	Cu	Mo	N
667827	0.0550	0.02	0.42	0.013	0.004	0.049	0.01	0.01	0.00	0.0058
	Ni	Nb	Ti	B	V	Ca				
	0.011	0.018	0.000	0.0001	0.001	0.0032				
TENSILE TEST										
Test Direction	Yield Strength	Tensile Strength	% Total Elong.							
L	60.7 ksi	67.1 ksi	33.0							

ThyssenKrupp Steel USA, LLC certify that the material herein described has been manufactured, sampled, tested and inspected in accordance with the contract requirements and is fully in compliance.

Bertram Ehrhardt
Director, Quality Assurance and Development

Rev.

Figure A-20. 3x1³/₄x7-gauge (76x44x4.6 mm), 81¹/₄-in. (2,064 mm) Long Midwest Weak Post with Holes, Post Nos. 3 through 25 and 62 through 74, Test No. MWP-9

12Ga. Tabbed Bracket Clips
MWP Clips R#16-0188 H#6464T3
White Paint



ESSAR STEEL ALGOMA INC., 105 West Street, Sault Ste. Marie, Ontario, Canada P6A 7B4

SO No., Item & Date:	8020680 000010 2014/04/14	Shipment No. & Date:	1000098384 2014/04/14	TC No., Date & Time:	ESA-149266 2014/04/15 - 02:10:17										
Sold to Customer Name and Address:	STATE STEEL SUPPLY CO. COURT STREET 214 SIOUX CITY, Iowa, USA 51102	Ship to Customer Name and Address:	STATE STEEL SUPPLY CO. COURT STREET 214 SIOUX CITY, Iowa, USA 51102	Customer PO No./Item:	P40213FJ901 / 1										
Customer Specification:			HR STEEL SHEET HSLA DQ / DS ASTM A1011 HSLAS-F GR 50 [2013] MOD CU .10 MAX Top Semi Critical Surface Improved Shape Restr Thickness 1/2 Tol												
Supplementary Instructions: Test Cert 1.tpx@statesteel.com															
Insp TIR: Test Report As Per Spec				Cust Use: VETTED RESALE											
ESSAR STEEL ALGOMA INC. HEREBY CERTIFIES THAT THE MATERIAL HEREIN DESCRIBED WAS MADE AND TESTED IN ACCORDANCE WITH THE RULES OF THE SPECIFICATION SHOWN. ALL RESULTS ARE RETAINED IN ACCORDANCE WITH THE COMPANY'S STANDARD RECORD KEEPING PRACTICES. THIS MILL TEST REPORT MAY NOT BE REPRODUCED EXCEPT IN FULL WITHOUT WRITTEN APPROVAL OF ESSAR STEEL ALGOMA, INC. IF YOU RECEIVE THIS DOCUMENT AND ARE NOT THE INTENDED RECEIVER, PLEASE CALL (705) 945-4065 FOR INSTRUCTIONS ON METHOD OF DISPOSAL OF DOCUMENT.															
MEETS EN 10204 3.1 ISO QUALITY AND ENVIRONMENTAL CERTIFICATES AVAILABLE AT WWW.ESSARSTEELALGOMA.COM															
ALL HEATS FULLY KILLED. HEATS INDICATED WITH (*) FINE GRAINED. HEATS INDICATED WITH (C) MADE IN CANADA WITH DOMESTIC AND NORTH AMERICAN MATERIALS.															
Dimensions (T x W x L)	Batch No.	Heat No.-MS	Quantity	No. of Pcs	Dimensions (T x W x L)	Batch No.	Heat No.-MS	Quantity	No. of Pcs						
0.0970" x 60.000"	TAP1178	6464T3-04	46,570 LB	1	0.0970" x 60.000"	SAP1179	6464T3-05	44,370 LB	1						
***** CHEMICAL PROPERTIES *****															
Heat No. (wt%)	C	Mn	P	S	SI	Cr	Ni	Cu	Mo	Al	Nb	V	Ti	N	Cs
6464T3*	0.05	0.46	0.009	0.002	0.020	0.02	0.01	0.02	0.00	0.025	0.005	0.038	0.001	0.0109	0.00330
***** MECHANICAL PROPERTIES *****															
Tensile Tests															
Heat No.	Batch No.	SRCE	LAB	GAUGE	COND	METH	DIR	LOC	YIELD(KSI)	TENSILE(KSI)	EL SCALE	ELONG(%)			
6464T3		DSPC	ALG	0.0970	AR	2	L	F	58.0	68.0	2"	30			



134

Figure A-22. 12-gauge Tabbed Bracket, Version 10, Test No. MWP-9

QUALITY CERTIFICATE

MWP Hardware

NINGBO JINDING FASTENING PIECE CO., LTD

R#16-0105

XIJINGTANG JIULONGHU NINGBO CHINA TEL: +86-574-86530122 FAX: +86-574-86530858

P#13055

Customer: FASTENAL COMPANY PURCHASING--IMPORT Date : 2015-01-09
 Product: HEX CAP SCREWS Contract No: 14JDF643T
 Class: 5 Invoice No: 00331052-1
 Size: 5/16-18X1 Lot No: 3324910004
 Marking: JDF three radius Order No. 100045659
 Quantity: 53.200 mpcs Part No. 13055
 Production Date 2014-11-05
 Certificate No.: 20141024022

Sept2015 SMT

Dimensions Of SPEC:

Inspection Items	Standard	Result	Sample	Pass
Visual Appearance	-----	OK	29	29
Body Diameter	/	/	5	5
Thread	Go	3A	OK	15
	No Go	2A	OK	15
Width Across Flats	0.500-0.489	0.490-0.494	5	5
Width Across Corners	0.577-0.557	0.571-0.567	5	5
Major Diameter	0.311-0.303	0.309-0.310	15	15
Head Height	0.211-0.195	0.201-0.207	5	5
Total Length	0.970-1.000	0.984-0.976	15	15
Thread Length	min 0.861	0.886-0.925	15	15
Key Engagement	/	/		
Head Diameter	/	/		

Mechanical Properties				
Characteristics	Standard	Result		
Surface Hardness [30N]	MAX 54	43-46	15	15
Core Hardness [HRC]	25-34	27-29	15	15
Wedge Strength [psi]	min 119880	140779-143536	5	5
Yield Strength [psi]	min 91869	108995-110446	5	5
Elongation [%]	min 14	17.4-17.7	5	5
Reduction Of area [%]	min 35	48.9-50.5	5	5
Proof Load [lb]	4450	4450	5	5
Impact test -20°C [AkV/J]	/	/		
Decarburization	N≥1/2HI HV0.3	299.54 299.54 308.46	5	5
HV2>=HV1-30, HV3<=HV1+30	G 0.0006max			

CHEMICAL COMPOSITION (%)											
Heat No	C	Si	Mn	P	S	Cr	Ni	Cu	Mo	B	
35#	0.36	0.18	0.67	0.018	0.009						
Thickness [UM]	min 5		10.2-7.73						29	29	
Surface Coating:	ZPCr3+(coating test method: X ray according to ASTM B568M 2007 standard test										
Thread Specification:	ASME B1.1 2008, UNIFIED INCH SCREW THREADS(UN AND UNR THREAD FORM)										
Sampling Dimension Specification:	ASME B18.18.2 2011 inspection and quality assurance for high-volume machine assembly										
Dimension Specification:	ASME B18.2.1 2012, HEX CAP SCREWS										
Sampling mechanical properties specification:	ASTM F1470 2012 Standard Guide for Fastener Sampling for Specified Mechanical										
Mechanical Properties:	SAE J429 2013, MECHANICAL AND MATERIAL REQUIREMENTS FOR EXTERNALLY THREADED FASTENERS										
Surface Defect:	ASTM F788/F788M, SURFACE DISCONTINUITIES OF BOLTS, SCREWS, AND STUDS										
Plating Specification:	ASTM 1941 2010, Electrodeposited Coatings On Threaded Fasteners										
Quality Control Supervisor							Quality Control Manager				



尹巍

Figure A-23. 5/16-in. (8-mm) Dia. UNC, 1-in. (25-mm) Long Hex Cap Screw, Test No. MWP-9

SUPER CHENG INDUSTRIAL CO.,LTD.

NO. 18 BEN-GONG 2nd ROAD., BEN CHOU INDUSTRIAL PARK, KAOHSIUNG COUNTY 820, TAIWAN R.O.C.
TEL : 886-7-6225326-30(5 LINES) FAX : 886-7-6215377/6212335/6235829

CERTIFICATE OF INSPECTION


CERT. # : S77-1411-02T ISSUED DATE : 2014/12/13 PAGE 1 OF 1

CLIENT : SUPER CHENG INDUSTRIAL CO., LTD.

ADDRESS : NO. 18 BEN-GONG 2nd ROAD., BEN CHOU INDUSTRIAL PARK, KAOHSIUNG COUNTY 820, TAIWAN R.O.C.

PURCHASER : FASTENAL COMPANY PURCHASING	PO # : 210085084
PART #36304	QTY SHIPPED : 162,000 PCS


COMMODITY : GRADE 5 FIN HEX NUT FINISH : TRIVALENT ZINC
 SIZE : 5/16-18 LOT# : S77-1411-02 SAMPLING PLAN : ANSI/ASME B18.18.2M-93
 QTY : 820000 PCS MATERIAL : SAE1010 HEAT NO. : 2QG45
 MANUFACTURER : SUPER CHENG IND. CO., LTD. MANU. DATE : 2014/11/15

DIMENSIONAL INSPECTION		SPEC. : ANSI/ASME B18.2.2-10		SAMPLED BY : FENG TE SU	
ITEM	SAMPLE SIZE	SPECIFIED		ACTUAL RESULT	JUDGMENT
APPEARANCE	100	ASTM F812-12		GOOD	OK
W.A.F.	32	0.500 ~ 0.489 in.		0.494 ~ 0.494 in.	OK
W.A.C.	8	0.577 ~ 0.557 in.		0.562 ~ 0.559 in.	OK
THICKNESS	8	0.273 ~ 0.258 in.		0.268 ~ 0.264 in.	OK
THREAD	32	ANSI/ASME B1.1		PASS	OK

MECHANICAL PROPERTIES		SPEC. : SAE J995-12		SAMPLED BY : FENG TE SU	
ITEM	SAMPLE SIZE	TEST METHOD	SPECIFIED	ACTUAL RESULT	JUDGMENT
HARDNESS	8	ASTM F606-13	MAX HRC32	12.0 ~ 9.0 HRC	PASS
PROOF LOAD	4	ASTM F606-13	MIN 6300LB	6493 ~ 6486 LB	PASS
PLATING THICKNESS	4	ASTM B568-98	MIN 0.0001 in	0.00023 ~ 0.00016 in	PASS

MWP Hardware
R#16-0105
Sept2015 SMT

- REMARK : 1、THIS REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL WITHOUT WRITTEN APPROVAL OF THE LAB.
 2、THIS INSPECTION CERTIFICATE IS FOR RESPONSIBILITY UNDER SAMPLE ONLY
 3、ABOVE SAMPLES TESTED CONFORM TO THE FASTENER SPECIFICATION OR STANDARDS




LAB. DIRECTOR(SIGNATORY) : _____

表單編號 : LQC 10E Rev.0

Figure A-24. 5/16-in. (8-mm) Nut, Test No. MWP-9

7 Gauge Sheet Steel
4CMwP Z-Posts
Red Paint

ThyssenKrupp Steel USA
1 ThyssenKrupp Drive
Calvert, AL 36513



Mill Certificate

CUSTOMER ORIGINAL

Order - Item 27519-221	Certificate Number 1118689850	Delivery No 80351618-10	Ship Date 03/06/2013	Page 1 of 1						
Customer No: 10780		Cust PO: 01010892								
Customer Part No: 27509										
Customer Sold to: Norfolk Iron & Metal Company 3001 North Victory Rd. NORFOLK NE 68702 USA		Customer Ship to: Norfolk Iron & Metal Company 3003 North Victory Rd. West Pt NORFOLK NE 68702 USA		Contact - Customer Service Company ThyssenKrupp Steel USA PO Box 456 CALVERT AL 36513 USA						
Steel Grade / Customer Specification HR15SLAS-F GRADE 50 [340] / 0.1750" X 60.0000" ACCORDING TO A1011 (light < 0.230"(6.0 mm))										
Type of Product/Surface HR Unexposed										
TEST METHOD ASTM										
MATERIAL DESCRIPTION										
	ORDERED	Heat No.	Coil No.	Weight Net LB	Weight Gross LB					
(mm)	4.445	106387	1118689850	59,149.030	59,149.030					
(in)	0.1750									
CHEMICAL COMPOSITION OF THE LADLE										
Heat No.	C	Si	Mn	P	S	Al	Cr	Cu	Mo	N
106387	0.0487	0.01	0.45	0.009	0.003	0.042	0.01	0.00	0.00	0.0048
	Ni	Nb	Ti	B	V	Ca				
	0.009	0.022	0.001	0.0001	0.001	0.003				
TENSILE TEST										
Heat No.	Coil No.	Test Direction	Yield Strength	Tensile Strength	% Total Elong.					
106387	1118689850	L	55.2 ksi	64.8 ksi	34.6					
n 0.176										

ThyssenKrupp Steel USA, LLC certify that the material herein described has been manufactured, sampled, tested and inspected in accordance with the contract requirements and is fully in compliance.

Bertram Ehrhardt
Director, Quality Assurance and Development

Figure A-25. 2¹/₈"x1³/₈"x7 Gauge [54x35x4.6], 6" [152] Long Bent Steel Plate, Test No. MWP-9

Customer Name UNL-MwRSF **Customer PO#** Paid by visa **Shipper No** 763182 **Heat Number** 198277.1.1

CERTIFIED TEST REPORT

Trip No. 223858 Bill of Lading: 161516 Packing Slip: 1625610 Ship Date: 06/10/2016
Customer No. 01293 Bill To: COPPER & BRASS SALES, PO BOX 5116, SOUTHFIELD, MI 48086-5116 Ship to: COPPER & BRASS SALES, 5230 ASHLAND WAY, FRANKLIN, WI 53132

IN-PROCESS OR FINISHED PRODUCT SAMPLES, AS INDICATED BELOW, HAVE BEEN ANALYZED AND TESTED AND FOUND TO CONFORM TO THE CHEMICAL AND PHYSICAL REQUIREMENTS OF THE SPECIFICATION INDICATED WITH THE FOLLOWING RESULTS

Copper	Lead	Iron	TOE	Zinc
ASTM B16/B16M-10 (2015) 60.0-63.0%	2.5-3.0%	0.35%max	0.50%max	Balance
CHEMICAL ANALYSIS STATEMENT OF CONFORMITY				
Chase Brass maintains chemical control according to the following statistical measures which are recalculated monthly:				
Cpk: 3.94	Lead: 1.61	Iron: 0.15	TOE: 0.31	Zinc: Balance
Mean: 61.38	Lead: 2.67	Iron: 0.26		
Max: 62.28	Lead: 2.98	Iron: 0.26		
Min: 60.46	Lead: 2.50	Iron: 0.26		

Order Traceability No	Product	Specification No	Customer PO	Quantity	Item No Custom Item No.
198277.10.1	C36000 ALLOY T.R. QUALITY H02 HALF HARD		5400307675/0100	2010	0406RD12 CURD00137
198277.11.1	C36000 ALLOY T.R. QUALITY H02 HALF HARD		5400307675/0110	1008	1437RD12 CURD00094
198277.12.1	C36000 ALLOY T.R. QUALITY H02 HALF HARD		5400307675/0120	2108	0547RD12 CURD00115
198277.13.1	C36000 ALLOY T.R. QUALITY H02 HALF HARD		5400307675/0130	1945	1812RD12 CURD01211
198277.15.1	C36000 ALLOY T.R. QUALITY H02 HALF HARD		5400307675/0150	1057	2000SQ12 CUSQ00099
198277.3.1	C36000 ALLOY T.R. QUALITY H02 HALF HARD		5400307675/0030	1033	0750HX12 CUHEX00033
198277.4.1	C36000 ALLOY T.R. QUALITY H02 HALF HARD		5400307675/0040	1067	1750RD12 CURD00967
198277.5.1	C36000 ALLOY T.R. QUALITY H02 HALF HARD		5400307675/0050	1018	1312RD12 CURD00067
198277.6.1	C36000 ALLOY T.R. QUALITY H02 HALF HARD		5400307675/0060	1986	0390RD12 CURD00198
198277.7.1	C36000 ALLOY T.R. QUALITY H02 HALF HARD		5400307675/0070	1500	0687HX12 CUHEX00245

Certified Mercury Free Material
ISO9001 Certified Quality System
Certificate Number: US006675-1 (Bureau Veritas Certification)
Material is Directive 2000/63/EC Compliant
Material is Directive 2002/95/EC (RoHS) Compliant
Material is Directive 2011/65/EU (RoHS2) Compliant
This test report meets the guidelines of EN 10204 2.1
Melted and manufactured in the USA
Chase produced rod: NAFTA - Yes

We hereby certify that the foregoing data is a true copy of the data furnished us by the producing mill or the data resulting from tests performed in the CHASE BRASS AND COPPER COMPANY, LLC LABORATORY.



Chase Brass and Copper Company, LLC
14212 Selwyn Drive
Montpelier, Ohio 43543-0152

By Jack A. Homer
Jack A. Homer
Quality Manager

From: ThyssenKrupp Materials NA
Cust. ONLINE METALS - TX
CstAr 4345
Wgt.: 9.793 LB

Del.: 2404792793
CstOr 64199
Date 09/28/2016

Tomas Sanchez

Figure A-26. Brass Straight Rod – 3/16-in. (5-mm) Cable Clip, Test No. MWP-9

Certificate of Quality

Date: 09/16/2016

BEKAERT CORPORATION Van Buren , Arkansas
1881 BEKAERT DRIVE
VAN BUREN, AR 72956
TEL(479)474-5211 FAX(479)474-9075
TELEFAX 537439

Customer	: Colorguard Rail Products	Our Order No	: 4210322864 / 000010
Final Customer	: Midwest Machinery & Supply Company	Product No	: AST3043SE10S02000 3/4 GUIDERAIL 3X7 200
Customer Order No	: 16-0831	QTY	: 3427.998 LBS
Customer Part No.	:	MFG SMP No	: AST3043SE10S02000
Customer Specification	: ASTM A 741		


Heat#	%C	%Mn	%P	%S	%Si
139920	0.64	0.62	0.008	0.021	0.18
139927	0.61	0.59	0.009	0.013	0.19
586105	0.64	0.70	0.007	0.015	0.20

Tag#	Heat#	Lay Length	Breaking Strength	Adherence Appearance of wires	Steel Ductility
		"	lbf		
		3.00	25000		
		7.50			
43750025	139920	6.74	42069	Pass	Pass
	139927				
43788809	139920	6.65	43514	Pass	Pass
	586105				

R#17-171 3/4" Guardrail Cable
Tag#43750025
October 2016 SMT

Made & Melted in USA.

The undersigned certifies that the results are actual results and conform to the standards as contained in the records of this Corporation.



David Berta
Quality Engineer

Notary Public

Figure A-27. 3/4-in. (19-mm) Diameter 3x7 Cable Guiderail, Test No. MWP-9


Certificate of Quality
BEKAERT CORPORATION Van Buren , Arkansas Date:03/28/2016

Customer : Colorguard Rail Products Our Order No : 4209973815 / 000010
 Final Customer : Midwest Machinery & Supply Company Product No : AST3043SE10S02000 3/4 GUIDERAIL 3X7 200

Tag#	Heat#	Lay Length	Breaking Strength	Adherence Appearance of wires	Steel Ductility
		"	lbf		
		3.00	25000		
		7.50			
43383706	139012 139024	6.12	43896	Pass	Pass
43383832	139012 139024	6.12	43896	Pass	Pass
43383972	139012 139024	6.31	43896	Pass	Pass
43383963	139012 139024	6.31	43896	Pass	Pass
43384097	139012 139024	6.31	43896	Pass	Pass
43384719	139015 139021	6.11	44100	Pass	Pass
43384721	139015 139021	6.11	44100	Pass	Pass
43384723	139015 139021	6.11	44100	Pass	Pass
43384728	139015 139021	6.20	44100	Pass	Pass
43384729	139015 139021	6.20	44100	Pass	Pass
43384730	139015 139021	6.20	44100	Pass	Pass
43384858	139016	6.14	44100	Pass	Pass
43384869	139016	6.14	44100	Pass	Pass
43385035	139016	6.14	44100	Pass	Pass
43385106	139012 139015	6.21	44100	Pass	Pass
43385126	139012 139015	6.21	44100	Pass	Pass
43385846	139012 139015	6.21	44100	Pass	Pass

Made & Melted in USA.

The undersigned certifies that the results are actual results and conform to the standards as contained in the records of this Corporation.




 David Berta
 Quality Engineer

 Notary Public

Figure A-28. 3/4-in. (19-mm) Diameter 3x7 Cable Guiderail, Test No. MWP-9

INSPECTION CERTIFICATE


4CMwP 7/8" Nuts
R# 14-0325 White Paint
Feb 2014 SMT

 **UNYTITE, INC.**
One Unytite Drive
Peru, Illinois 61354
815-224-2221 — FAX# 815-224-3434

Customer	Specification	Size	Lot No.	Date
BENNETT BOLT WORKS 12 ELBRIDGE STREET JORDAN, N.Y. 13080	ASTM A-563 GRADE DH HEAVY HEX NUT	7/8 - 9 UNC	MW471	Aug. 19, '08

Mechanical properties tested in accordance to ASTM F606/F606M, ASTM A370, ASTM E18

Chemical Composition (%)												Shape & Dimension	ANSI B18.2.2		
Mill Maker	Material Size	Heat No.	Spec.	C	Si	Mn	P	S	Cu	Ni	Cr			Mo	Inspection
GERDAU AMER	CARBON			0.20	MIN.	MAX.	MAX.							Thread Precision	ANSI B1.1 CLASS 2B GOOD
	ISTEEL (NO	STEEL	M643354	0.55	0.60	0.040	0.050	-	-	-	-	-	Inspection		
				0.45	0.20	0.70	0.009	0.029	0.24	0.12	0.07	0.03		Appearance	
Mechanical Property Inspection												Heat Treatment	Inspection	GOOD	
Item	Proof Load	Cone Stripping	Hardness	Hardness	Absorbed Energy										
Spec.	80,850	-	24-38									T: MIN. 800 P			
	lbf	kN • kgf • lbf	HxC	HxB • HB	J • kgfm • ftlbf										
Results	n	n										Q: FORGING Q (W.Q.)	Remarks:		
	5	-	27.1									T: 1149 F/45M. (W.C.)	"DH U"		
	Results	Results	27.5									Q: Quenching T: Tempering ST: Solution Treatment	Production Quantity 71,940 pcs.		
	GOOD	-	27.6												
			27.3												
				Hardness Treatment											
				After 24 Hr.X	*F (*C)										


 OFFICIAL SEAL
 JEAN MARGHERIO
 NOTARY PUBLIC - STATE OF ILLINOIS
 MY COMMISSION EXPIRES 10/18/09
 08-20-08

Material used for the nut was melted and manufactured in the USA. The nut was manufactured in the USA to the above specification.

We hereby certify that the material described has been manufactured and inspected satisfactorily with the requirement of the above specification.

Chief of Quality Assurance Section

141

Figure A-29. 7/8-in. (22-mm) Dia. Hex Nut, Test No. MWP-9




TC Industries Test Center
3703 South Route 31
Crystal Lake, IL 60012-1412
Telephone (815) 459-2400 Fax (815) 459-3419

TEST REPORT

REPORT NO: 168646
DATE: JULY 30, 2013
PAGE 1 OF 1

BILL TO: AMERICAN EAGLE STEEL
317 EAST 11TH STREET
CHICAGO HEIGHTS, IL 60411

SHIP TO: AMERICAN EAGLE STEEL
317 EAST 11TH STREET
CHICAGO HEIGHTS, IL 60411

DESC: 362 PCS .875"RD X 24'		HEAT: 133079		GRADE: 1045		WT: 17740	
PO: 1563-TC		MO: 60190		CO: 1563		LOT: 88006	
SPEC: QUENCH,TEMPER,STRAIGHTEN PINK ENDS				ASTM A449-10			
PROCESS:		FURN TEMP: 1600		FURN TIME hh.mm: 1.00		QUENCH: WATER	
		TEMPER TEMP: 1125		TEMPER TIME hh.mm: 1.00			
		STRESS TEMP:		STRESS TIME hh.mm:			
PARAMETER	UNITS	LIMITS		TEST RESULTS			
TENSILE	KSI	120.0	N/A	143.0			
YIELD .2%	KSI	92.0	N/A	130.0			
ELONG 2"	%	14.0	N/A	17.0			
RED AREA	%	35.0	N/A	48.0			
SURF HB	HBW	255	321	282	285	285	293
				285	285		
4CMwP Cable End Threaded Rod A449/1045 White Paint for Left Red Paint for Right Bennett Bolt Lot# 83219(left)83218(right) Feb 2014 R#14-0325 SMT							
 ACCREDITED Testing Cert #1281-01							

TC INDUSTRIES and SUBCONTRACTED LABS (A2LA ACCREDITED)			
Tensile, Standard TC	Rockwell	Micro Analysis	
Tensile, Full Size	Brinell TC	Decarb Measure	
Charpy V Notch	Ultra Sonic*	Chemistry*	
Microhardness, Knoop*	Bend Test*		
TC: TC Test Center	BE: Berg Eng.	EX: Exova	MSI: Metallurgical Ser.
Cert #1281.01	Cert #L1157-1	Cert #104.02	Cert #0510.01
2/28/15	2/4/14	6/30/14	12/31/14

Time 17:38 DATE IN: 7/20/13 *not included in our scope of accreditation FC 4.12.16F 7/15/10
NOTES:

Ken Rueff

Ken Rueff
Test Center Supervisor

There are no deviations from test methods unless noted. It should not be assumed that mechanical properties of raw material heat treated to a test standard will have the same properties of a finished testpiece whose original material characteristics may have been significantly altered.
No mercury was used/added and no welding/weld repair was performed on this material while in the possession of TC Industries, Inc.
This test report relates only to the items tested and shall not be reproduced, except in full, without the written permission of TC Industries Test Center.

Figure A-30. Cable End Threaded Rod, Test No. MWP-9

09/27/2007 10:02 3156893999
SEP-28-2007 10:13AM FROM-Buck Co. HR

BENNETT BOLT WORKS
717-284-4321

PAGE 04
T-131 P.004/004 F-840



BUCK COMPANY, INC.

897 Lancaster Pike, Quarryville, PA 17566-9738

Phone (717) 284-4114 Fax (717) 284-4321

www.buckcompany.com greatercastings@buckcompany.com

MATERIAL CERTIFICATION

Date 8-30-07 Form# CERT-7A Rev C 4-21-06
CUSTOMER Bennett Bolt, Inc
ORDER NUMBER 75590
PATTERN NUMBER CGBBWTH REV. —

This is to certify that the castings listed conform to the following specifications and comply in all respects with the drawing or ordered requirements. All Quality Assurance provisions and / or Quality Assurance requirements and / or supplementary Quality Assurance provisions have been completed and accepted. SPC data is on file and available upon request.

Type Material: malleable Iron
Specifications: Asm-A47
Grade or Class: 32510
Heat Number: 904

MECHANICAL PROPERTIES
Tensile Str. PSI 45,062
Yield Str. PSI 45,032
Elongation 22

PHYSICAL PROPERTIES
Brinell Hardness 163
PCS SHIPPED 20
1 of 1

CHEMICAL ANALYSIS
Total Carbon 3.70
Silicon 2.87
Manganese .34
Sulfur .017
Phosphorus .020
Chromium .043
Magnesium .019
Copper .052

DATE SHIPPED 8-30-07
[Signature]
Quality Assurance Representative

Quality Castings
ISO 9001:2000 CERTIFIED
Ferritic and Pearlitic Malleable Iron, Gray and Ductile Iron, Brass, Aluminum

Figure A-31. Bennett Cable End Fitter, H# 9Q4, Test No. MWP-9

09/27/2007 10:02 3156893999
SEP-26-2007 10:13AM FROM-Buck Co. HR

BENNETT BOLT WORKS
717-284-4321

PAGE 05
T-131 P.003/004 F-840



BUCK COMPANY, INC.

897 Lancaster Pike, Quarryville, PA 17566-9738
Phone (717) 284-4114 Fax (717) 284-4321

www.buckcompany.com grescastings@buckcompany.com

MATERIAL CERTIFICATION

Date 11/14/06 Form Number CERT-7C REV. A
CUSTOMER: Bennett Bolt Works
ORDER NUMBER 75410
PATTERN NUMBER CGBBHT REV. —

This is to certify that the castings listed conform to the following specifications and comply in all respects with the drawing or ordered requirements. All Quality Assurance provisions and / or Quality Assurance requirements and / or supplementary Quality Assurance provisions have been completed and accepted. SPC data is on file and available upon request. Melted & Manufactured in the USA.

Type Material: malleable Iron
Specifications: ASTM-A47
Grade or Class: 32510
Heat Number: OP5

MECHANICAL PROPERTIES
Tensile Str. PSI 57112
Yield Str. PSI 35584
Elongation 15

PHYSICAL PROPERTIES
Brinell Hardness 121
PCS SHIPPED 105

1 of 1

CHEMICAL ANALYSIS
Total Carbon 2.53
Silicon 1.51
Manganese .33
Sulfur .030
Phosphorus .015
Chrome .03%
Magnesium .001
Copper .115

DATE SHIPPED 11/14/06
[Signature]
Quality Assurance Representative

Quality Castings
ISO 9001 CERTIFIED

Permal and Permalite Malleable Iron, Gray and Ductile Iron - Brass - Aluminum

Figure A-32. Bennett Cable End Fitter, H# OP5, Test No. MWP-9



Cable Wedges H#DA8 R#15-0635

June 2015 SMT

BUCK COMPANY, INC.

897 Lancaster Pike, Quarryville, PA 17566-9738

Phone (717) 284-4114 Fax (717) 284-4321

www.buckcompany.com

greatcastings@buckcompany.com

MATERIAL CERTIFICATION

Date 4/28/14

Form# CERT-7C Rev A 4/21/06

CUSTOMER: Bennett Bolt

ORDER NUMBER 6011934

PATTERN NUMBER W1 Wedge

This is to certify that the castings listed conform to the following specifications and comply in all respects with the drawing or ordered requirements. All Quality Assurance provisions and / or Quality Assurance requirements and / or supplementary Quality Assurance provisions have been completed and accepted. SPC data is on file and available upon request. Melted & Manufactured in the USA.

Type Material: Malleable Iron

Specifications: ASTM - A41

Grade or Class: 32510

Heat Number: DA8

MECHANICAL PROPERTIES

Tensile Str. PSI 53,665

Yield Str. PSI 35,031

Elongation 14

PHYSICAL PROPERTIES

Brinell Hardness 126

PCS SHIPPED 9,698

1 OF 1

CHEMICAL ANALYSIS

Total Carbon	<u>2.61</u>
Silicon	<u>1.56</u>
Manganese	<u>.38</u>
Sulfur	<u>.113</u>
Phosphorus	<u>.014</u>
Chrome	<u>.039</u>
Magnesium	<u>.001</u>
Copper	<u>.373</u>

DATE SHIPPED 4/25/14

Wanda Lopez
Quality Assurance Representative

Quality Castings
ISO 9001: 2008 CERTIFIED
Ferritic and Pearlitic Malleable Iron, Gray and Ductile Iron, Brass, Aluminum

Figure A-33. Cable Wedges, Test No. MWP-9

10/05/99 15:05 ☎14409920360

KEN FORGING

002/002



OCTOBER 5, 1999

BENNETT BOLT WORKS, INC.
12 ELBRIDGE STREET
JORDAN, NY 13080

4CMwP Turnbuckles
R# 14-0325 White Paint
Bennett Bolt Lot# 21331/18305
COC Feb 2014 SMT

CERIFICATION OF CONFORMANCE

THIS LETTER IS TO ADVISE THE **TURNBUCKLES** NOTED BELOW ARE
MANUFACTURED IN THE UNITED STATES OF AMERICA BY KEN FORGING,
INC,

THESE TURNBUCKLES ARE MANUFACTURED IN COMPLIANCE WITH
FEDERAL SPECIFICATION FF-T-791 1b TYPE 1

PURCHASED ORDER NO. 7158

PART NUMBER : TB109-G TB110-G

QUANTITY SHIPPED: 8PCS. 100PCS

DATE SHIPPED: 9/8/99

KEN FORGING, INC.

Clark Landa

1049 Griggs Road • Post Office Box 277 • Jefferson, OH 44047
(440) 993-8091 • Fax: (440) 992-0360

Figure A-34. Bennet Short Threaded Turnbuckle, Test No. MWP-9

Appendix B. Vehicle Center of Gravity Determination




Figure B-1. Vehicle Mass Distribution, Test No. MWP-9

Appendix C. Static Soil Tests







Figure C-1. Soil Strength, Initial Calibration Tests, Test No. MWP-9



Date.....	10/28/2016
Test Facility & Site Location.....	Midwest Roadside Safety Facility
In situ soil description (ASTM D2487).....	Well-Graded Gravel (GW)
Fill material description (ASTM D2487).....	Well-Graded Gravel (GW) (see sieve analyses above)
Description of fill placement procedure.....	8-inch lifts tamped with a pneumatic compactor

Figure C-2. Static Soil Test, Test No. MWP-9

Appendix D. Vehicle Deformation Records

VEHICLE PRE/POST CRUSH
FLOORPAN - SET 1

TEST: MWP-9
VEHICLE: Kia Rio

POINT	X (in.)	Y (in.)	Z (in.)	X' (in.)	Y' (in.)	Z' (in.)	ΔX (in.)	ΔY (in.)	ΔZ (in.)
1	27.427	-21.827	2.170	27.115	-21.982	2.282	-0.311	-0.154	0.112
2	29.795	-15.642	-1.253	29.559	-15.849	-1.093	-0.236	-0.208	0.160
3	29.322	-11.554	-1.773	29.077	-11.791	-1.629	-0.245	-0.237	0.144
4	28.814	-5.764	-1.983	28.566	-6.016	-1.890	-0.248	-0.253	0.092
5	25.889	-22.018	-1.637	25.658	-22.241	-1.424	-0.230	-0.223	0.213
6	26.287	-15.713	-2.978	26.106	-15.963	-2.809	-0.181	-0.249	0.169
7	26.042	-11.446	-3.387	25.893	-11.703	-3.211	-0.149	-0.257	0.176
8	25.780	-6.028	-3.528	25.596	-6.304	-3.419	-0.183	-0.275	0.109
9	20.076	-21.637	-4.868	19.906	-21.899	-4.748	-0.169	-0.263	0.120
10	19.706	-15.577	-4.742	19.555	-15.795	-4.662	-0.152	-0.217	0.079
11	19.831	-11.280	-5.036	19.565	-11.414	-4.958	-0.267	-0.134	0.078
12	18.999	-5.988	-4.860	18.765	-6.156	-4.801	-0.234	-0.168	0.058
13	16.142	-21.997	-5.123	15.939	-22.212	-5.036	-0.203	-0.215	0.087
14	15.940	-15.776	-4.732	15.798	-16.105	-4.678	-0.142	-0.329	0.053
15	15.444	-10.914	-4.759	15.246	-11.140	-4.573	-0.198	-0.226	0.186
16	15.241	-6.008	-5.124	15.095	-6.257	-5.018	-0.146	-0.249	0.106
17	12.524	-21.990	-5.142	12.344	-22.222	-5.115	-0.181	-0.232	0.028
18	12.068	-15.903	-4.473	11.874	-16.192	-4.427	-0.194	-0.289	0.046
19	11.460	-10.907	-4.481	11.211	-11.249	-4.278	-0.250	-0.342	0.203
20	11.127	-6.478	-5.090	10.988	-6.783	-4.871	-0.138	-0.305	0.218
21	8.503	-21.855	-4.758	8.193	-22.131	-4.729	-0.310	-0.276	0.029
22	8.367	-15.929	-4.181	8.186	-16.191	-4.163	-0.181	-0.262	0.018
23	8.337	-11.133	-4.205	8.125	-11.407	-4.110	-0.211	-0.275	0.095
24	8.222	-6.275	-4.735	8.070	-6.541	-4.729	-0.152	-0.266	0.006
25	0.326	-21.830	0.175	0.036	-22.098	0.166	-0.290	-0.268	-0.009
26	0.267	-15.890	-0.022	-0.014	-15.993	-0.031	-0.281	-0.103	-0.009
27	0.127	-10.692	-0.047	-0.060	-10.913	-0.067	-0.187	-0.221	-0.020
28	0.000	-5.278	0.026	-0.093	-5.446	-0.028	-0.093	-0.169	-0.054




Figure D-1. Floor pan Deformation Data – Set 1, Test No. MWP-9

VEHICLE PRE/POST CRUSH
FLOORPAN - SET 2

TEST: MWP-9
VEHICLE: Kia Rio

POINT	X (in.)	Y (in.)	Z (in.)	X' (in.)	Y' (in.)	Z' (in.)	ΔX (in.)	ΔY (in.)	ΔZ (in.)
1	41.889	-24.564	3.894	41.798	-24.529	3.884	-0.091	0.035	-0.010
2	44.665	-18.437	0.796	44.598	-18.393	0.706	-0.067	0.043	-0.090
3	44.365	-14.346	0.310	44.265	-14.320	0.238	-0.100	0.026	-0.072
4	44.103	-8.547	0.189	44.015	-8.458	0.131	-0.088	0.089	-0.058
5	40.625	-24.650	0.088	40.547	-24.561	-0.032	-0.078	0.088	-0.120
6	41.311	-18.331	-1.143	41.233	-18.384	-1.226	-0.078	-0.053	-0.084
7	41.267	-14.097	-1.464	41.154	-14.087	-1.547	-0.114	0.010	-0.083
8	41.229	-8.674	-1.519	41.026	-8.582	-1.642	-0.203	0.092	-0.123
9	35.083	-24.010	-3.526	35.054	-23.983	-3.646	-0.030	0.027	-0.121
10	34.991	-17.882	-3.319	34.844	-17.944	-3.439	-0.147	-0.063	-0.120
11	35.083	-13.622	-3.526	35.025	-13.573	-3.628	-0.058	0.049	-0.102
12	34.413	-8.294	-3.298	34.353	-8.319	-3.389	-0.060	-0.025	-0.091
13	31.179	-24.177	-4.039	31.047	-24.115	-4.183	-0.132	0.062	-0.145
14	31.210	-18.094	-3.551	31.000	-18.120	-3.684	-0.210	-0.026	-0.133
15	30.835	-13.092	-3.517	30.751	-13.172	-3.490	-0.084	-0.080	0.027
16	30.873	-8.262	-3.821	30.628	-8.268	-3.826	-0.245	-0.006	-0.005
17	27.536	-24.072	-4.289	27.531	-24.157	-4.463	-0.005	-0.085	-0.174
18	27.228	-18.000	-3.546	27.141	-18.016	-3.664	-0.086	-0.016	-0.118
19	26.712	-13.011	-3.481	26.614	-13.117	-3.436	-0.098	-0.107	0.045
20	26.617	-8.550	-4.050	26.466	-8.637	-3.933	-0.152	-0.088	0.118
21	23.404	-23.797	-4.179	23.393	-23.920	-4.334	-0.011	-0.123	-0.156
22	23.582	-17.914	-3.510	23.392	-17.997	-3.621	-0.190	-0.083	-0.112
23	23.736	-13.160	-3.437	23.542	-13.199	-3.456	-0.193	-0.039	-0.019
24	23.838	-8.229	-3.888	23.634	-8.274	-3.950	-0.205	-0.046	-0.063
25	15.128	-23.576	0.191	14.908	-23.702	0.077	-0.220	-0.125	-0.114
26	15.181	-17.471	0.131	15.103	-17.666	0.025	-0.078	-0.195	-0.106
27	15.278	-12.417	0.193	15.067	-12.558	0.114	-0.212	-0.140	-0.079
28	15.464	-6.936	0.332	15.194	-7.069	0.299	-0.271	-0.133	-0.032




Figure D-2. Floor pan Deformation Data – Set 2, Test No. MWP-9




Figure D-3. Occupant Compartment Deformation Data – Set 1, Test No. MWP-9

VEHICLE PRE/POST CRUSH
INTERIOR CRUSH - SET 2

TEST: MWP-9
VEHICLE: Kia Rio

	POINT	X (in.)	Y (in.)	Z (in.)	X' (in.)	Y' (in.)	Z' (in.)	ΔX (in.)	ΔY (in.)	ΔZ (in.)
DASH	1	28.997	-26.331	23.676	28.846	-26.138	23.446	-0.151	0.193	-0.230
	2	25.859	-15.129	27.385	25.710	-15.039	27.346	-0.148	0.091	-0.039
	3	28.707	-0.884	24.992	28.490	-0.687	24.899	-0.217	0.197	-0.093
	4	28.188	-24.468	13.618	28.073	-24.319	13.369	-0.116	0.149	-0.249
	5	28.199	-14.734	13.019	28.076	-14.600	12.877	-0.123	0.134	-0.142
	6	25.807	-1.830	12.513	25.543	-1.767	12.491	-0.264	0.063	-0.021
SIDE PANEL	7	37.830	-28.614	8.048	37.670	-28.509	7.902	-0.160	0.105	-0.145
	8	33.649	-28.545	4.666	33.631	-28.487	4.364	-0.018	0.058	-0.302
	9	37.294	-28.539	1.987	37.166	-28.510	1.919	-0.128	0.029	-0.068
IMPACT SIDE DOOR	10	2.108	-29.129	24.782	1.856	-29.558	24.627	-0.252	-0.428	-0.155
	11	14.657	-29.309	23.699	14.513	-29.784	23.628	-0.144	-0.475	-0.071
	12	27.186	-29.598	22.516	26.985	-29.771	22.454	-0.200	-0.174	-0.062
	13	4.386	-29.524	7.226	4.266	-29.752	7.095	-0.120	-0.227	-0.130
	14	18.963	-30.005	7.366	18.790	-30.190	7.240	-0.173	-0.185	-0.126
	15	31.526	-29.594	6.730	31.424	-29.482	6.606	-0.102	0.113	-0.124
ROOF	1	15.639	-20.636	39.909	15.977	-20.071	40.045	0.338	0.565	0.137
	2	16.545	-14.734	40.258	16.790	-14.838	41.060	0.245	-0.104	0.802
	3	16.982	-10.377	40.430	17.128	-10.446	41.069	0.146	-0.069	0.639
	4	17.321	-5.745	40.551	17.287	-5.810	41.098	-0.034	-0.065	0.547
	5	17.369	-2.024	40.653	17.249	-2.157	41.098	-0.120	-0.133	0.445
	6	8.998	-19.772	42.560	9.162	-19.702	42.651	0.165	0.070	0.091
	7	9.950	-14.843	42.858	9.973	-14.908	42.323	0.024	-0.065	-0.535
	8	9.914	-10.169	43.235	9.861	-10.252	42.498	-0.054	-0.083	-0.737
	9	10.099	-5.666	43.429	9.934	-5.789	42.880	-0.165	-0.123	-0.549
	10	9.975	-1.533	43.550	9.785	-1.629	42.995	-0.190	-0.096	-0.555
	11	2.681	-18.443	43.709	2.788	-18.579	43.136	0.107	-0.136	-0.573
	12	3.112	-14.005	44.061	3.029	-14.108	42.493	-0.083	-0.103	-1.568
	13	2.866	-9.667	44.378	2.788	-9.786	42.522	-0.078	-0.119	-1.856
	14	2.984	-5.842	44.523	2.749	-5.918	42.866	-0.235	-0.077	-1.657
	15	2.763	-2.360	44.652	2.636	-2.482	43.059	-0.127	-0.122	-1.594




Figure D-4. Occupant Compartment Deformation Data – Set 2, Test No. MWP-9




Figure D-5. Exterior Vehicle Crush (NASS) - Front, Test No. MWP-9




Figure D-6. Exterior Vehicle Crush (NASS) - Side, Test No. MWP-9

Appendix E. Accelerometer and Rate Transducer Data Plots, Test No. MWP-9




Figure E-1. 10-ms Average Longitudinal Deceleration (SLICE-1), Test No. MWP-9




Figure E-2. Longitudinal Occupant Velocity (SLICE-1), Test No. MWP-9




Figure E-3. Longitudinal Occupant Displacement (SLICE-1), Test No. MWP-9




Figure E-4. 10-ms Average Lateral Deceleration (SLICE-1), Test No. MWP-9




Figure E-5. Lateral Occupant Impact Velocity (SLICE-1), Test No. MWP-9




Figure E-6. Lateral Occupant Displacement (SLICE-1), Test No. MWP-9




Figure E-7. Vehicle Angular Displacements (SLICE-1), Test No. MWP-9




Figure E-8. Acceleration Severity Index (SLICE-1), Test No. MWP-9




Figure E-9. 10-ms Average Longitudinal Deceleration (SLICE-2), Test No. MWP-9




Figure E-10. Longitudinal Occupant Impact Velocity (SLICE-2), Test No. MWP-9




Figure E-11. Longitudinal Occupant Displacement (SLICE-2), Test No. MWP-9




Figure E-12. 10-ms Average Lateral Deceleration (SLICE-2), Test No. MWP-9




Figure E-13. Lateral Occupant Impact Velocity (SLICE-2), Test No. MWP-9




Figure E-14. Lateral Occupant Displacement (SLICE-2), Test No. MWP-9




Figure E-15. Vehicle Angular Displacements (SLICE-2), Test No. MWP-9




Figure E-16. Acceleration Severity Index (SLICE-2), Test No. MWP-9

Appendix F. Load Cell and String Potentiometer Data




Figure F-1. Load Cell Data, Cable No. 1, Test No. MWP-9




Figure F-2. Load Cell Data, Cable No. 2, Test No. MWP-9




Figure F-3. Load Cell Data, Cable No. 3, Test No. MWP-9




Figure F-4. Load Cell Data, Cable No. 4, Test No. MWP-9




Figure F-5. String Potentiometer Data, Upstream Anchor, Test No. MWP-9

END OF DOCUMENT